

BIPV - DESIGN WITH SOLAR CELLS

**DIFFERENT SOLAR CELLS
LAYOUTS**

GLASS TYPES


LAMINATED SOLAR GLASS



Laminated glass raises the bar for contemporary building and is a symbol of refinement and safety. This novel material redefines architectural possibilities with its unmatched strength, impact resistance, and smooth, exquisite finish. It is made of layers linked together. In today's architectural world, laminated glass is the cornerstone of current architecture, seamlessly fusing safety and style. Its benefits range from improving structural integrity to offering soundproofing and security.


These Laminated Glass layers can exhibit various configurations such as the following:

LAMINATED SOLAR GLASS LAYERS		
	IMPERIAL	METRIC
a./e. Low Iron Glass	0.11in (Opaque only), 0.15in, & 0.23in	3mm (Opaque only), 4mm, & 6mm
b./d./x. Encapsulant	Ethylene Vinyl Acetate: Good radiation transmission and low degradability to sunlight as an encapsulating agent or other interlayer specified.	
c. Solar Cells	Mono-crystalline (6.25in X 6.25in)	Mono-crystalline (158.75mm X 158.75mm)
z. Backsheet (Optional)	High durability, UV resistant, PV backsheet	



GLASS TYPES


DOUBLE LAYER INSULATED GLASS UNIT (IGU)



As architectural solutions progress, Insulated Glass Units (IGUs) become a revolutionary invention that redefines the purpose of windows and facades. These state-of-the-art units, made of several glass panes divided by an insulating gas-filled gap, transform buildings with their increased comfort, noise reduction, and greater thermal efficiency. IGUs are a crucial component of sustainable and cozy living spaces since they improve energy efficiency while also adding a contemporary aesthetic touch.

This Insulated Glass Units features a Laminated Solar Glass as a first layer plus a spacer and a second Laminated Solar Glass layer. These layers can exhibit various configurations, such as the following:

DOUBLE LAYER INSULATED GLASS UNIT (IGU)		
	IMPERIAL	METRIC
a./e./g. Low Iron Glass	0.11in (Opaque only), 0.15in, & 0.23in	3mm (Opaque only), 4mm, & 6mm
b./d./x. Encapsulant	Ethylene Vinyl Acetate: Good radiation transmission and low degradability to sunlight as an encapsulating agent or other interlayer specified.	
c. Solar Cells	Mono-crystalline (6.25in X 6.25in)	Mono-crystalline (158.75mm X 158.75mm)
z. Backsheet (Optional)	High durability, UV resistant, PV backsheet	
f. Spacer	0.47in, (0.23in to 0.98in)	12mm, (6mm to 25mm)



GLASS TYPES


TRIPLE LAYER INSULATED GLASS UNIT (IGU)



This innovative development raises the bar for comfort and energy efficiency to never-before-seen heights. This technique, which consists of three layers of glass divided by insulating voids, raises the bar for environmental sustainability, soundproofing, and thermal insulation. For the most demanding architectural designs and ecologically sensitive settings, the triple-layer IGU is more than just a window—it's a testament to excellent performance, providing enhanced comfort, noise reduction, and exceptional energy efficiency.

This Insulated Glass Units features a Laminated Solar Glass as a first layer, a spacer, a second Laminated Solar Glass layer and a third laminated glass layer. These layers can exhibit various configurations, such as the following:


TRIPLE LAYER INSULATED GLASS UNIT (IGU)		
	IMPERIAL	METRIC
a./e./g./i. Low Iron Glass	0.11in (Opaque only), 0.15in, & 0.23in	3mm (Opaque only), 4mm, & 6mm
b./d./x. Encapsulant	Ethylene Vinyl Acetate: Good radiation transmission and low degradability to sunlight as an encapsulating agent or other interlayer specified.	
c. Solar Cells	Mono-crystalline (6.25in X 6.25in)	Mono-crystalline (158.75mm X 158.75mm)
z. Backsheet (Optional)	High durability, UV resistant, PV backsheet	
f./h. Spacer	0.47in, (0.23in to 0.98in)	12mm, (6mm to 25mm)




MITREX SOLAR GLASS

STANDARD AND CUSTOM SIZES


RECTANGULAR SHAPE




SQUARE SHAPE



CIRCULAR SHAPE




EQUILATERAL TRIANGLE SHAPE




MITREX SOLAR GLASS

STANDARD AND CUSTOM SIZES


ISOSCELES TRIANGLE SHAPE



HEXAGONAL SHAPE





PARALLELOGRAM SHAPE



GLASS SHAPES

RECTANGULAR


FLAT STANDARD SIZE



Mitrex standard flat glass panels serve as versatile canvases for integrating various solar cell arrangements, providing a spectrum of options for harnessing solar energy.

CURVED STANDARD SIZE



Mitrex standard curved glass panel, set at a subtle 20-degree angle, offers a sleek and contemporary aesthetic while also providing a unique platform for solar cell arrangements. Different solar cell configurations can be strategically placed across the glass surface, maximizing sunlight absorption throughout the day.



GLASS SHAPES

SQUARE


FLAT STANDARD SIZE



Mitrex's square-shaped flat glass panels offer a flexible platform for incorporating different configurations of solar cells, presenting a wide range of possibilities for capturing solar energy.

CURVED STANDARD SIZE



Mitrex's square-shaped curved glass panels, angled at 20 degrees, offer a sleek design and a unique platform for placing solar cells strategically, maximizing sunlight absorption.



GLASS SHAPES

CIRCULAR


FLAT STANDARD SIZE



Mitrex's circular-shaped flat glass panels provide versatility for integrating various arrangements of solar cells, offering numerous opportunities to capture solar energy.

CURVED STANDARD SIZE



Mitrex circular-shaped curved glass panel, set at a subtle 20-degree angle, offers a sleek and contemporary aesthetic while also providing a unique platform for solar cell arrangements. Different solar cell configurations can be strategically placed across the glass surface, maximizing sunlight absorption throughout the day.



GLASS SHAPES

ISOSCELES TRIANGLE


FLAT STANDARD SIZE



Mitrex Isosceles flat glass panels offer distinct design possibilities for integrating diverse solar cell arrangements, catering to both aesthetic appeal and power optimization. The isosceles panels, with their asymmetrical shape, enable creative placements of solar cells, allowing for unique and unconventional configurations that can enhance the visual appeal of structures.

CURVED STANDARD SIZE



Mitrex's triangular-shaped curved glass panels, angled at 20 degrees, offer a sleek design and a unique platform for placing solar cells strategically, maximizing sunlight absorption.



GLASS SHAPES

EQUILATERAL TRIANGLE


FLAT STANDARD SIZE



Mitrex equilateral flat glass panels offer distinct design possibilities for integrating diverse solar cell arrangements, catering to both aesthetic appeal and power optimization. Equilateral panels, on the other hand, provide a symmetrical and uniform canvas for arranging solar cells in standard or tailored patterns, maximizing power generation while maintaining a clean and consistent design.

CURVED STANDARD SIZE



Mitrex's triangular-shaped curved glass panels, angled at 20 degrees, offer a sleek design and a unique platform for placing solar cells strategically, maximizing sunlight absorption.



GLASS SHAPES

HEXAGONAL


FLAT STANDARD SIZE



Mitrex hexagonal glass shapes represent a dynamic canvas for integrating diverse solar cell arrangements, offering an innovative blend of design flexibility and enhanced power generation. The unique geometry of hexagonal panels allows for creative configurations of solar cells, adapting seamlessly to unconventional patterns that augment both the aesthetics and functionality of installations.

CURVED STANDARD SIZE



Mitrex's hexagonal-shaped curved glass panels, angled at 20 degrees, offer a sleek design and a unique platform for placing solar cells strategically, maximizing sunlight absorption.



GLASS SHAPES

PARALLELOGRAM


FLAT STANDARD SIZE



Mitrex parallelogram-shaped glass panels introduce a new dimension of design versatility, offering a canvas for diverse solar cell arrangements that amplify both the aesthetic allure and energy efficiency of structures. The unique angles and lines of parallelogram panels provide an unconventional yet adaptable space for creative configurations of solar cells. This shape allows for tailored arrangements, maximizing exposure to sunlight and optimizing energy generation.


CURVED STANDARD SIZE

Mitrex's parallelogram-shaped curved glass panels, angled at 20 degrees, offer a sleek design and a unique platform for placing solar cells strategically, maximizing sunlight absorption.




CELL ARRANGEMENTS


RECTANGULAR SHAPE




A1




A2




A3



A4




A5




A6

CELL ARRANGEMENTS


RECTANGULAR SHAPE




A7




A8




A21



A22




A23




A24

CELL ARRANGEMENTS


RECTANGULAR SHAPE




A25




A26




A27



A31




A32




A33

CELL ARRANGEMENTS


RECTANGULAR SHAPE




A34




A111




A112



A113




A114




A115

CELL ARRANGEMENTS


RECTANGULAR SHAPE




A116




A121




A122



A123




A124




A125

CELL ARRANGEMENTS


RECTANGULAR SHAPE




A126




A127




A128



A41




A42




A43

CELL ARRANGEMENTS


RECTANGULAR SHAPE




A44




A45




A46



A51




A52




A53

CELL ARRANGEMENTS


RECTANGULAR SHAPE



A54




A55




A56

CELL ARRANGEMENTS


SQUARE SHAPE




B1




B2




B3




B4




B5




B6



B7




B8




B21

CELL ARRANGEMENTS


SQUARE SHAPE




B22




B23




B24




B25




B26




B31



B32




B33




B34

CELL ARRANGEMENTS

SQUARE SHAPE




B35




B36

CELL ARRANGEMENTS


CIRCULAR SHAPE




C11




C12




C13




C21




C22




C23



C24




C25




C31

CELL ARRANGEMENTS


CIRCULAR SHAPE




C32




C33




C34




C35




C36




C41



C42




C43




C51

CELL ARRANGEMENTS


CIRCULAR SHAPE




C52



C53




C54




C55

CELL ARRANGEMENTS


ISOSCELES TRIANGULE SHAPE



C14




C15




C16

CELL ARRANGEMENTS


EQUILATERAL TRIANGLE SHAPE




C61




C62




C63




C64




C65




C66



C71




C72




C73

CELL ARRANGEMENTS


EQUILATERAL TRIANGLE SHAPE



C74




C75




C76

CELL ARRANGEMENTS


HEXAGONAL SHAPE




C17




C18




C19




C81




C82




C83



C84




C85




C91

CELL ARRANGEMENTS


HEXAGONAL SHAPE




C92




C93



C94




C95




C96

CELL ARRANGEMENTS


PARALLELOGRAM SHAPE




C101




C102




C103




C104




C105




C106



C111




C112




C113

CELL ARRANGEMENTS


PARALLELOGRAM SHAPE



C114



C115



C116

SOLAR GLASS & JUNCTION BOX

LAMINATED SOLAR GLASS


In the Mitrex solar glass, the position of the junction box can be at the front, top or back of the glass depending on the project needs.

Placing the junction box on the top surface ensures easy accessibility for maintenance and inspection, simplifying wiring and connections while preserving the clean appearance of the glass front.

On the other hand, a front-mounted junction box allows for convenient access while maintaining a sleek and integrated look. However, it might be more visible, impacting the overall aesthetics.

Additionally, positioning the junction box at the back conceals wiring and connections, providing a streamlined and unobstructed front surface, enhancing the visual appeal of the structure. The choice of placement involves a careful balance between accessibility, aesthetics, and functionality, each position influencing the efficiency and visual impact of the solar setup.


JUNCTION BOX ON TOP




SOLAR GLASS & JUNCTION BOX

LAMINATED SOLAR GLASS

JUNCTION BOX ON THE FACE




JUNCTION BOX AT THE BACK




SOLAR GLASS & JUNCTION BOX

IGU SOLAR GLASS DOUBLE LAYER

JUNCTION BOX ON TOP




JUNCTION BOX ON THE FACE




SOLAR GLASS & JUNCTION BOX

IGU SOLAR GLASS TRIPLE LAYER

JUNCTION BOX ON TOP



JUNCTION BOX ON THE FACE



TECHNICAL DATA

GLASS DATASHEET

Non-Active Models

Panel Type	Layers						UV %	Visible Light Transmittance	Total Solar Transmittance	Visible		Solar Heat Gain Coefficient	U-Value (BTU/hrft2F)			Light to Solar Gain
	Class L1	Class L2	Spacer	Class L3	Spacer	Class L4				Exterior	Interior		Winter	Summer	Daytime	
	Thickness	Thickness	Size	Thickness	Size	Thickness							Nighttime	Daytime		
LowIron-LowIron	3	3	N/A	N/A	N/A	N/A	0%	91%	83%	8%	8%	86%	1.00	0.90	1.06	
LowIron-LowIron	4	4	N/A	N/A	N/A	N/A	1%	91%	82%	8%	8%	85%	0.99	0.90	1.07	
LowIron-LowIron	6	6	N/A	N/A	N/A	N/A	0%	90%	81%	8%	8%	85%	0.97	0.88	1.06	
LowIron-LowIronLowE	3	3	N/A	N/A	N/A	N/A	0%	76%	38%	10%	9%	45%	1.00	0.90	1.69	
LowIron-LowIronLowE	4	4	N/A	N/A	N/A	N/A	0%	76%	38%	10%	9%	45%	0.99	0.90	1.69	
LowIron-LowIronLowE	6	6	N/A	N/A	N/A	N/A	0%	76%	38%	10%	9%	46%	0.97	0.88	1.65	
LowIron-LowIron-Spacer-Clear	3	3	12	3	N/A	N/A	0%	82%	70%	15%	15%	76%	0.45	0.47	1.08	
LowIron-LowIron-Spacer-Clear	4	4	12	4	N/A	N/A	1%	82%	68%	15%	15%	75%	0.44	0.47	1.09	
LowIron-LowIron-Spacer-Clear	6	6	12	6	N/A	N/A	0%	81%	63%	15%	15%	73%	0.44	0.46	1.11	
LowIron-LowIron-Spacer-LowIron	3	3	12	3	N/A	N/A	0%	84%	76%	15%	15%	78%	0.45	0.47	1.08	
LowIron-LowIron-Spacer-LowIron	4	4	12	4	N/A	N/A	1%	83%	75%	15%	15%	77%	0.44	0.47	1.08	
LowIron-LowIron-Spacer-LowIron	6	6	12	6	N/A	N/A	0%	83%	73%	15%	15%	76%	0.44	0.46	1.09	
LowIron-LowIron-Spacer-LowEClear	3	3	12	3	N/A	N/A	0%	73%	37%	12%	11%	48%	0.24	0.22	1.52	
LowIron-LowIron-Spacer-LowEClear	4	4	12	4	N/A	N/A	0%	73%	36%	12%	11%	48%	0.24	0.22	1.52	
LowIron-LowIron-Spacer-LowEClear	6	6	12	6	N/A	N/A	0%	72%	35%	12%	11%	48%	0.24	0.22	1.50	
LowIron-LowIron-Spacer-LowELowIron	3	3	12	3	N/A	N/A	0%	75%	38%	12%	11%	48%	0.29	0.27	1.56	
LowIron-LowIron-Spacer-LowELowIron	4	4	12	4	N/A	N/A	0%	75%	38%	12%	11%	48%	0.28	0.26	1.56	
LowIron-LowIron-Spacer-LowELowIron	6	6	12	6	N/A	N/A	0%	74%	38%	12%	11%	48%	0.24	0.22	1.54	
LowIron-LowIron-Spacer-Clear-Spacer-Clear	3	3	12	3	12	3	0%	75%	59%	21%	21%	68%	0.29	0.32	1.10	
LowIron-LowIron-Spacer-Clear-Spacer-Clear	4	4	12	4	12	4	1%	74%	56%	21%	21%	67%	0.28	0.32	1.10	
LowIron-LowIron-Spacer-Clear-Spacer-Clear	6	6	12	6	12	6	0%	72%	50%	21%	20%	64%	0.28	0.32	1.13	
LowIron-LowIron-Spacer-LowIron-Spacer-LowIron	3	3	12	3	12	3	0%	77%	69%	21%	21%	72%	0.29	0.32	1.07	
LowIron-LowIron-Spacer-LowIron-Spacer-LowIron	4	4	12	4	12	4	1%	77%	68%	21%	21%	71%	0.28	0.32	1.08	
LowIron-LowIron-Spacer-LowIron-Spacer-LowIron	6	6	12	6	12	6	0%	77%	66%	21%	21%	70%	0.28	0.32	1.10	
LowIron-LowIron-Spacer-LowEClear-Spacer-LowEClear	3	3	12	3	12	3	0%	59%	25%	15%	13%	39%	0.12	0.12	1.51	
LowIron-LowIron-Spacer-LowEClear-Spacer-LowEClear	4	4	12	4	12	4	0%	58%	25%	14%	12%	39%	0.12	0.12	1.49	
LowIron-LowIron-Spacer-LowEClear-Spacer-LowEClear	6	6	12	6	12	6	0%	57%	24%	14%	12%	38%	0.12	0.12	1.50	
LowIron-LowIron-Spacer-LowELowIron-Spacer-LowELowIron	3	3	12	3	12	3	0%	61%	27%	15%	13%	40%	0.12	0.12	1.53	
LowIron-LowIron-Spacer-LowELowIron-Spacer-LowELowIron	4	4	12	4	12	4	0%	61%	27%	15%	13%	40%	0.12	0.12	1.53	
LowIron-LowIron-Spacer-LowELowIron-Spacer-LowELowIron	6	6	12	6	12	6	0%	60%	27%	15%	13%	39%	0.12	0.12	1.54	

Panel Layers LowIron-LowIron			Layers						UV %	Visible Light Transmittance	Total Solar Transmittance	Visible Reflectance		Solar Heat Gain Coefficient	U-Value (BTU/hrft2F)		Light to Solar Gain
Panel Type	Shape	Cell Coverage Area	Glass L1 Thickness	Glass L2 Thickness	Spacer Size	Glass L3 Thickness	Spacer Size	Glass L4 Thickness				Exterior	Interior		Winter Nighttime	Summer Daytime	
C74	Triangle	47%	3	3	N/A	N/A	N/A	N/A	0%	48%	44%	18%	18%	45%	1.00	0.90	1.06
C75	Triangle	37%	3	3	N/A	N/A	N/A	N/A	0%	57%	52%	16%	16%	54%	1.00	0.90	1.06
C76	Triangle	41%	3	3	N/A	N/A	N/A	N/A	0%	53%	49%	17%	17%	50%	1.00	0.90	1.06
C17	Hexagon	48%	3	3	N/A	N/A	N/A	N/A	0%	47%	43%	19%	19%	44%	1.00	0.90	1.06
C18	Hexagon	32%	3	3	N/A	N/A	N/A	N/A	0%	62%	56%	15%	15%	58%	1.00	0.90	1.06
C19	Hexagon	16%	3	3	N/A	N/A	N/A	N/A	0%	76%	70%	12%	12%	72%	1.00	0.90	1.06
C81	Hexagon	68%	3	3	N/A	N/A	N/A	N/A	0%	29%	27%	23%	23%	28%	1.00	0.90	1.06
C82	Hexagon	36%	3	3	N/A	N/A	N/A	N/A	0%	58%	53%	16%	16%	55%	1.00	0.90	1.06
C83	Hexagon	36%	3	3	N/A	N/A	N/A	N/A	0%	58%	53%	16%	16%	55%	1.00	0.90	1.06
C84	Hexagon	52%	3	3	N/A	N/A	N/A	N/A	0%	43%	40%	19%	19%	41%	1.00	0.90	1.06
C85	Hexagon	22%	3	3	N/A	N/A	N/A	N/A	0%	71%	65%	13%	13%	67%	1.00	0.90	1.06
C91	Hexagon	69%	3	3	N/A	N/A	N/A	N/A	0%	28%	26%	23%	23%	27%	1.00	0.90	1.06
C92	Hexagon	53%	3	3	N/A	N/A	N/A	N/A	0%	43%	39%	20%	20%	40%	1.00	0.90	1.06
C93	Hexagon	37%	3	3	N/A	N/A	N/A	N/A	0%	57%	52%	16%	16%	54%	1.00	0.90	1.06
C94	Hexagon	10%	3	3	N/A	N/A	N/A	N/A	0%	82%	75%	10%	10%	78%	1.00	0.90	1.06
C95	Hexagon	32%	3	3	N/A	N/A	N/A	N/A	0%	62%	57%	15%	15%	59%	1.00	0.90	1.06
C96	Hexagon	47%	3	3	N/A	N/A	N/A	N/A	0%	48%	44%	18%	18%	45%	1.00	0.90	1.06
C101	Parallelogram	63%	3	3	N/A	N/A	N/A	N/A	0%	34%	31%	22%	22%	32%	1.00	0.90	1.06
C102	Parallelogram	30%	3	3	N/A	N/A	N/A	N/A	0%	64%	58%	15%	15%	60%	1.00	0.90	1.06
C103	Parallelogram	37%	3	3	N/A	N/A	N/A	N/A	0%	58%	53%	16%	16%	55%	1.00	0.90	1.06
C104	Parallelogram	32%	3	3	N/A	N/A	N/A	N/A	0%	62%	57%	15%	15%	59%	1.00	0.90	1.06
C105	Parallelogram	23%	3	3	N/A	N/A	N/A	N/A	0%	70%	64%	13%	13%	66%	1.00	0.90	1.06
C106	Parallelogram	50%	3	3	N/A	N/A	N/A	N/A	0%	46%	42%	19%	19%	43%	1.00	0.90	1.06
C111	Parallelogram	53%	3	3	N/A	N/A	N/A	N/A	0%	43%	39%	20%	20%	40%	1.00	0.90	1.06
C112	Parallelogram	40%	3	3	N/A	N/A	N/A	N/A	0%	55%	50%	17%	17%	52%	1.00	0.90	1.06
C113	Parallelogram	43%	3	3	N/A	N/A	N/A	N/A	0%	52%	47%	18%	18%	49%	1.00	0.90	1.06
C114	Parallelogram	27%	3	3	N/A	N/A	N/A	N/A	0%	67%	61%	14%	14%	63%	1.00	0.90	1.06
C115	Parallelogram	40%	3	3	N/A	N/A	N/A	N/A	0%	55%	50%	17%	17%	52%	1.00	0.90	1.06
C116	Parallelogram	27%	3	3	N/A	N/A	N/A	N/A	0%	67%	61%	14%	14%	63%	1.00	0.90	1.06

Panel Layers			Layers						UV %	Visible Light Transmittance	Total Solar Transmittance	Visible Reflectance		Solar Heat Gain Coefficient	U-Value (BTU/hrft2F)		Light to Solar Gain
LowIron-LowIron			Class L1	Class L2	Spacer	Class L3	Spacer	Class L4				Exterior	Interior		Winter Nighttime	Summer Daytime	
Panel Type	Shape	Cell Coverage Area	Thickness	Thickness	Size	Thickness	Size	Thickness									
C74	Triangle	47%	4	4	N/A	N/A	N/A	N/A	1%	48%	43%	18%	18%	45%	0.99	0.90	1.07
C75	Triangle	37%	4	4	N/A	N/A	N/A	N/A	1%	57%	52%	16%	16%	54%	0.99	0.90	1.07
C76	Triangle	41%	4	4	N/A	N/A	N/A	N/A	1%	53%	48%	17%	17%	50%	0.99	0.90	1.07
C17	Hexagon	48%	4	4	N/A	N/A	N/A	N/A	1%	47%	42%	19%	19%	44%	0.99	0.90	1.07
C18	Hexagon	32%	4	4	N/A	N/A	N/A	N/A	1%	62%	56%	15%	15%	58%	0.99	0.90	1.07
C19	Hexagon	16%	4	4	N/A	N/A	N/A	N/A	1%	76%	69%	12%	12%	71%	0.99	0.90	1.07
C81	Hexagon	68%	4	4	N/A	N/A	N/A	N/A	0%	29%	26%	23%	23%	27%	0.99	0.90	1.07
C82	Hexagon	36%	4	4	N/A	N/A	N/A	N/A	1%	58%	52%	16%	16%	54%	0.99	0.90	1.07
C83	Hexagon	36%	4	4	N/A	N/A	N/A	N/A	1%	58%	52%	16%	16%	54%	0.99	0.90	1.07
C84	Hexagon	52%	4	4	N/A	N/A	N/A	N/A	0%	43%	39%	19%	19%	41%	0.99	0.90	1.07
C85	Hexagon	22%	4	4	N/A	N/A	N/A	N/A	1%	71%	64%	13%	13%	67%	0.99	0.90	1.07
C91	Hexagon	69%	4	4	N/A	N/A	N/A	N/A	0%	28%	25%	23%	23%	26%	0.99	0.90	1.07
C92	Hexagon	53%	4	4	N/A	N/A	N/A	N/A	0%	43%	38%	20%	20%	40%	0.99	0.90	1.07
C93	Hexagon	37%	4	4	N/A	N/A	N/A	N/A	1%	57%	51%	16%	16%	53%	0.99	0.90	1.07
C94	Hexagon	10%	4	4	N/A	N/A	N/A	N/A	1%	82%	74%	10%	10%	77%	0.99	0.90	1.07
C95	Hexagon	32%	4	4	N/A	N/A	N/A	N/A	1%	62%	56%	15%	15%	58%	0.99	0.90	1.07
C96	Hexagon	47%	4	4	N/A	N/A	N/A	N/A	1%	48%	43%	18%	18%	45%	0.99	0.90	1.07
C101	Parallelogram	63%	4	4	N/A	N/A	N/A	N/A	0%	34%	30%	22%	22%	31%	0.99	0.90	1.07
C102	Parallelogram	30%	4	4	N/A	N/A	N/A	N/A	1%	64%	57%	15%	15%	60%	0.99	0.90	1.07
C103	Parallelogram	37%	4	4	N/A	N/A	N/A	N/A	1%	58%	52%	16%	16%	54%	0.99	0.90	1.07
C104	Parallelogram	32%	4	4	N/A	N/A	N/A	N/A	1%	62%	56%	15%	15%	58%	0.99	0.90	1.07
C105	Parallelogram	23%	4	4	N/A	N/A	N/A	N/A	1%	70%	63%	13%	13%	65%	0.99	0.90	1.07
C106	Parallelogram	50%	4	4	N/A	N/A	N/A	N/A	1%	46%	41%	19%	19%	43%	0.99	0.90	1.07
C111	Parallelogram	53%	4	4	N/A	N/A	N/A	N/A	0%	43%	38%	20%	20%	40%	0.99	0.90	1.07
C112	Parallelogram	40%	4	4	N/A	N/A	N/A	N/A	1%	55%	49%	17%	17%	51%	0.99	0.90	1.07
C113	Parallelogram	43%	4	4	N/A	N/A	N/A	N/A	1%	52%	47%	18%	18%	48%	0.99	0.90	1.07
C114	Parallelogram	27%	4	4	N/A	N/A	N/A	N/A	1%	67%	60%	14%	14%	62%	0.99	0.90	1.07
C115	Parallelogram	40%	4	4	N/A	N/A	N/A	N/A	1%	55%	49%	17%	17%	51%	0.99	0.90	1.07
C116	Parallelogram	27%	4	4	N/A	N/A	N/A	N/A	1%	67%	60%	14%	14%	62%	0.99	0.90	1.07

Panel Layers LowIron-LowIron			Layers							UV %	Visible Light Transmittance	Total Solar Transmittance	Visible Reflectance		Solar Heat Gain Coefficient	U-Value (BTU/hrft2F)		Light to Solar Gain
Panel Type	Shape	Cell Coverage Area	Glass L1 Thickness	Glass L2 Thickness	Spacer Size	Glass L3 Thickness	Spacer Size	Glass L4 Thickness	Exterior				Interior	Winter Nighttime		Summer Daytime		
C74	Triangle	47%	6	6	N/A	N/A	N/A	N/A	0%	47%	43%	18%	18%	45%	0.97	0.88	1.06	
C75	Triangle	37%	6	6	N/A	N/A	N/A	N/A	0%	57%	51%	16%	16%	54%	0.97	0.88	1.06	
C76	Triangle	41%	6	6	N/A	N/A	N/A	N/A	0%	53%	47%	17%	17%	50%	0.97	0.88	1.06	
C17	Hexagon	48%	6	6	N/A	N/A	N/A	N/A	0%	47%	42%	19%	19%	44%	0.97	0.88	1.06	
C18	Hexagon	32%	6	6	N/A	N/A	N/A	N/A	0%	61%	55%	15%	15%	58%	0.97	0.88	1.06	
C19	Hexagon	16%	6	6	N/A	N/A	N/A	N/A	0%	76%	68%	12%	12%	71%	0.97	0.88	1.06	
C81	Hexagon	68%	6	6	N/A	N/A	N/A	N/A	0%	29%	26%	23%	23%	27%	0.97	0.88	1.06	
C82	Hexagon	36%	6	6	N/A	N/A	N/A	N/A	0%	57%	51%	16%	16%	54%	0.97	0.88	1.06	
C83	Hexagon	36%	6	6	N/A	N/A	N/A	N/A	0%	57%	51%	16%	16%	54%	0.97	0.88	1.06	
C84	Hexagon	52%	6	6	N/A	N/A	N/A	N/A	0%	43%	39%	19%	19%	41%	0.97	0.88	1.06	
C85	Hexagon	22%	6	6	N/A	N/A	N/A	N/A	0%	70%	63%	13%	13%	67%	0.97	0.88	1.06	
C91	Hexagon	69%	6	6	N/A	N/A	N/A	N/A	0%	28%	25%	23%	23%	26%	0.97	0.88	1.06	
C92	Hexagon	53%	6	6	N/A	N/A	N/A	N/A	0%	42%	38%	20%	20%	40%	0.97	0.88	1.06	
C93	Hexagon	37%	6	6	N/A	N/A	N/A	N/A	0%	56%	51%	16%	16%	53%	0.97	0.88	1.06	
C94	Hexagon	10%	6	6	N/A	N/A	N/A	N/A	0%	81%	73%	10%	10%	77%	0.97	0.88	1.06	
C95	Hexagon	32%	6	6	N/A	N/A	N/A	N/A	0%	62%	55%	15%	15%	58%	0.97	0.88	1.06	
C96	Hexagon	47%	6	6	N/A	N/A	N/A	N/A	0%	47%	43%	18%	18%	45%	0.97	0.88	1.06	
C101	Parallelogram	63%	6	6	N/A	N/A	N/A	N/A	0%	33%	30%	22%	22%	31%	0.97	0.88	1.06	
C102	Parallelogram	30%	6	6	N/A	N/A	N/A	N/A	0%	63%	57%	15%	15%	60%	0.97	0.88	1.06	
C103	Parallelogram	37%	6	6	N/A	N/A	N/A	N/A	0%	57%	51%	16%	16%	54%	0.97	0.88	1.06	
C104	Parallelogram	32%	6	6	N/A	N/A	N/A	N/A	0%	62%	55%	15%	15%	58%	0.97	0.88	1.06	
C105	Parallelogram	23%	6	6	N/A	N/A	N/A	N/A	0%	69%	62%	13%	13%	65%	0.97	0.88	1.06	
C106	Parallelogram	50%	6	6	N/A	N/A	N/A	N/A	0%	45%	41%	19%	19%	43%	0.97	0.88	1.06	
C111	Parallelogram	53%	6	6	N/A	N/A	N/A	N/A	0%	42%	38%	20%	20%	40%	0.97	0.88	1.06	
C112	Parallelogram	40%	6	6	N/A	N/A	N/A	N/A	0%	54%	49%	17%	17%	51%	0.97	0.88	1.06	
C113	Parallelogram	43%	6	6	N/A	N/A	N/A	N/A	0%	51%	46%	18%	18%	48%	0.97	0.88	1.06	
C114	Parallelogram	27%	6	6	N/A	N/A	N/A	N/A	0%	66%	59%	14%	14%	62%	0.97	0.88	1.06	
C115	Parallelogram	40%	6	6	N/A	N/A	N/A	N/A	0%	54%	49%	17%	17%	51%	0.97	0.88	1.06	
C116	Parallelogram	27%	6	6	N/A	N/A	N/A	N/A	0%	66%	59%	14%	14%	62%	0.97	0.88	1.06	

Panel Layers			Layers							UV %	Visible Light Transmittance	Total Solar Transmittance	Visible Reflectance		Solar Heat Gain Coefficient	U-Value (BTU/hrft ² F)		Light to Solar Gain
LowIron-LowIronLowE			Class L1	Class L2	Spacer	Class L3	Spacer	Class L4	Exterior				Interior	Winter Nighttime		Summer Daytime		
Panel Type	Shape	Cell Coverage Area	Thickness	Thickness	Size	Thickness	Size	Thickness										
C74	Triangle	47%	3	3	N/A	N/A	N/A	N/A	0%	40%	20%	19%	19%	24%	1.00	0.90	1.69	
C75	Triangle	37%	3	3	N/A	N/A	N/A	N/A	0%	48%	24%	17%	17%	28%	1.00	0.90	1.69	
C76	Triangle	41%	3	3	N/A	N/A	N/A	N/A	0%	45%	22%	18%	18%	26%	1.00	0.90	1.69	
C17	Hexagon	48%	3	3	N/A	N/A	N/A	N/A	0%	39%	20%	20%	19%	23%	1.00	0.90	1.69	
C18	Hexagon	32%	3	3	N/A	N/A	N/A	N/A	0%	52%	26%	16%	16%	31%	1.00	0.90	1.69	
C19	Hexagon	16%	3	3	N/A	N/A	N/A	N/A	0%	64%	32%	13%	12%	38%	1.00	0.90	1.69	
C81	Hexagon	68%	3	3	N/A	N/A	N/A	N/A	0%	24%	12%	24%	23%	14%	1.00	0.90	1.69	
C82	Hexagon	36%	3	3	N/A	N/A	N/A	N/A	0%	48%	24%	17%	17%	29%	1.00	0.90	1.69	
C83	Hexagon	36%	3	3	N/A	N/A	N/A	N/A	0%	48%	24%	17%	17%	29%	1.00	0.90	1.69	
C84	Hexagon	52%	3	3	N/A	N/A	N/A	N/A	0%	36%	18%	20%	20%	21%	1.00	0.90	1.69	
C85	Hexagon	22%	3	3	N/A	N/A	N/A	N/A	0%	60%	30%	14%	14%	35%	1.00	0.90	1.69	
C91	Hexagon	69%	3	3	N/A	N/A	N/A	N/A	0%	24%	12%	24%	23%	14%	1.00	0.90	1.69	
C92	Hexagon	53%	3	3	N/A	N/A	N/A	N/A	0%	36%	18%	21%	20%	21%	1.00	0.90	1.69	
C93	Hexagon	37%	3	3	N/A	N/A	N/A	N/A	0%	48%	24%	17%	17%	28%	1.00	0.90	1.69	
C94	Hexagon	10%	3	3	N/A	N/A	N/A	N/A	0%	69%	34%	12%	11%	41%	1.00	0.90	1.69	
C95	Hexagon	32%	3	3	N/A	N/A	N/A	N/A	0%	52%	26%	16%	16%	31%	1.00	0.90	1.69	
C96	Hexagon	47%	3	3	N/A	N/A	N/A	N/A	0%	40%	20%	19%	19%	24%	1.00	0.90	1.69	
C101	Parallelogram	63%	3	3	N/A	N/A	N/A	N/A	0%	28%	14%	23%	22%	17%	1.00	0.90	1.69	
C102	Parallelogram	30%	3	3	N/A	N/A	N/A	N/A	0%	53%	27%	16%	15%	32%	1.00	0.90	1.69	
C103	Parallelogram	37%	3	3	N/A	N/A	N/A	N/A	0%	48%	24%	17%	17%	29%	1.00	0.90	1.69	
C104	Parallelogram	32%	3	3	N/A	N/A	N/A	N/A	0%	52%	26%	16%	16%	31%	1.00	0.90	1.69	
C105	Parallelogram	23%	3	3	N/A	N/A	N/A	N/A	0%	58%	29%	15%	14%	35%	1.00	0.90	1.69	
C106	Parallelogram	50%	3	3	N/A	N/A	N/A	N/A	0%	38%	19%	20%	19%	23%	1.00	0.90	1.69	
C111	Parallelogram	53%	3	3	N/A	N/A	N/A	N/A	0%	36%	18%	21%	20%	21%	1.00	0.90	1.69	
C112	Parallelogram	40%	3	3	N/A	N/A	N/A	N/A	0%	46%	23%	18%	17%	27%	1.00	0.90	1.69	
C113	Parallelogram	43%	3	3	N/A	N/A	N/A	N/A	0%	43%	22%	19%	18%	26%	1.00	0.90	1.69	
C114	Parallelogram	27%	3	3	N/A	N/A	N/A	N/A	0%	56%	28%	15%	15%	33%	1.00	0.90	1.69	
C115	Parallelogram	40%	3	3	N/A	N/A	N/A	N/A	0%	46%	23%	18%	17%	27%	1.00	0.90	1.69	
C116	Parallelogram	27%	3	3	N/A	N/A	N/A	N/A	0%	56%	28%	15%	15%	33%	1.00	0.90	1.69	

Panel Layers			Layers							UV %	Visible Light Transmittance	Total Solar Transmittance	Visible Reflectance		Solar Heat Gain Coefficient	U-Value (BTU/hrft2F)		Light to Solar Gain
LowIron-LowIronLowE			Class L1 Thickness	Class L2 Thickness	Spacer Size	Class L3 Thickness	Spacer Size	Class L4 Thickness	Exterior				Interior	Winter Nighttime		Summer Daytime		
Panel Type	Shape	Cell Coverage Area																
C74	Triangle	47%	4	4	N/A	N/A	N/A	N/A	0%	40%	20%	19%	19%	24%	0.99	0.90	1.69	
C75	Triangle	37%	4	4	N/A	N/A	N/A	N/A	0%	48%	24%	17%	17%	28%	0.99	0.90	1.69	
C76	Triangle	41%	4	4	N/A	N/A	N/A	N/A	0%	45%	22%	18%	18%	26%	0.99	0.90	1.69	
C17	Hexagon	48%	4	4	N/A	N/A	N/A	N/A	0%	39%	20%	20%	19%	23%	0.99	0.90	1.69	
C18	Hexagon	32%	4	4	N/A	N/A	N/A	N/A	0%	52%	26%	16%	16%	31%	0.99	0.90	1.69	
C19	Hexagon	16%	4	4	N/A	N/A	N/A	N/A	0%	64%	32%	13%	12%	38%	0.99	0.90	1.69	
C81	Hexagon	68%	4	4	N/A	N/A	N/A	N/A	0%	24%	12%	24%	23%	14%	0.99	0.90	1.69	
C82	Hexagon	36%	4	4	N/A	N/A	N/A	N/A	0%	48%	24%	17%	17%	29%	0.99	0.90	1.69	
C83	Hexagon	36%	4	4	N/A	N/A	N/A	N/A	0%	48%	24%	17%	17%	29%	0.99	0.90	1.69	
C84	Hexagon	52%	4	4	N/A	N/A	N/A	N/A	0%	36%	18%	20%	20%	21%	0.99	0.90	1.69	
C85	Hexagon	22%	4	4	N/A	N/A	N/A	N/A	0%	60%	30%	14%	14%	35%	0.99	0.90	1.69	
C91	Hexagon	69%	4	4	N/A	N/A	N/A	N/A	0%	24%	12%	24%	23%	14%	0.99	0.90	1.69	
C92	Hexagon	53%	4	4	N/A	N/A	N/A	N/A	0%	36%	18%	21%	20%	21%	0.99	0.90	1.69	
C93	Hexagon	37%	4	4	N/A	N/A	N/A	N/A	0%	48%	24%	17%	17%	28%	0.99	0.90	1.69	
C94	Hexagon	10%	4	4	N/A	N/A	N/A	N/A	0%	69%	34%	12%	11%	41%	0.99	0.90	1.69	
C95	Hexagon	32%	4	4	N/A	N/A	N/A	N/A	0%	52%	26%	16%	16%	31%	0.99	0.90	1.69	
C96	Hexagon	47%	4	4	N/A	N/A	N/A	N/A	0%	40%	20%	19%	19%	24%	0.99	0.90	1.69	
C101	Parallelogram	63%	4	4	N/A	N/A	N/A	N/A	0%	28%	14%	23%	22%	17%	0.99	0.90	1.69	
C102	Parallelogram	30%	4	4	N/A	N/A	N/A	N/A	0%	53%	27%	16%	15%	32%	0.99	0.90	1.69	
C103	Parallelogram	37%	4	4	N/A	N/A	N/A	N/A	0%	48%	24%	17%	17%	29%	0.99	0.90	1.69	
C104	Parallelogram	32%	4	4	N/A	N/A	N/A	N/A	0%	52%	26%	16%	16%	31%	0.99	0.90	1.69	
C105	Parallelogram	23%	4	4	N/A	N/A	N/A	N/A	0%	58%	29%	15%	14%	35%	0.99	0.90	1.69	
C106	Parallelogram	50%	4	4	N/A	N/A	N/A	N/A	0%	38%	19%	20%	19%	23%	0.99	0.90	1.69	
C111	Parallelogram	53%	4	4	N/A	N/A	N/A	N/A	0%	36%	18%	21%	20%	21%	0.99	0.90	1.69	
C112	Parallelogram	40%	4	4	N/A	N/A	N/A	N/A	0%	46%	23%	18%	17%	27%	0.99	0.90	1.69	
C113	Parallelogram	43%	4	4	N/A	N/A	N/A	N/A	0%	43%	22%	19%	18%	26%	0.99	0.90	1.69	
C114	Parallelogram	27%	4	4	N/A	N/A	N/A	N/A	0%	56%	28%	15%	15%	33%	0.99	0.90	1.69	
C115	Parallelogram	40%	4	4	N/A	N/A	N/A	N/A	0%	46%	23%	18%	17%	27%	0.99	0.90	1.69	
C116	Parallelogram	27%	4	4	N/A	N/A	N/A	N/A	0%	56%	28%	15%	15%	33%	0.99	0.90	1.69	

Panel Layers			Layers						UV %	Visible Light Transmittance	Total Solar Transmittance	Visible Reflectance		Solar Heat Gain Coefficient	U-Value (BTU/hrft2F)		Light to Solar Gain
LowIron-LowIronLowE			Class L1	Class L2	Spacer	Class L3	Spacer	Class L4				Exterior	Interior		Winter Nighttime	Summer Daytime	
Panel Type	Shape	Cell Coverage Area	Thickness	Thickness	Size	Thickness	Size	Thickness									
C74	Triangle	47%	6	6	N/A	N/A	N/A	N/A	0%	40%	20%	19%	19%	24%	0.97	0.88	1.65
C75	Triangle	37%	6	6	N/A	N/A	N/A	N/A	0%	48%	24%	17%	17%	29%	0.97	0.88	1.65
C76	Triangle	41%	6	6	N/A	N/A	N/A	N/A	0%	45%	22%	18%	18%	27%	0.97	0.88	1.65
C17	Hexagon	48%	6	6	N/A	N/A	N/A	N/A	0%	39%	20%	20%	19%	24%	0.97	0.88	1.65
C18	Hexagon	32%	6	6	N/A	N/A	N/A	N/A	0%	52%	26%	16%	16%	31%	0.97	0.88	1.65
C19	Hexagon	16%	6	6	N/A	N/A	N/A	N/A	0%	64%	32%	13%	12%	39%	0.97	0.88	1.65
C81	Hexagon	68%	6	6	N/A	N/A	N/A	N/A	0%	24%	12%	24%	23%	15%	0.97	0.88	1.65
C82	Hexagon	36%	6	6	N/A	N/A	N/A	N/A	0%	48%	24%	17%	17%	29%	0.97	0.88	1.65
C83	Hexagon	36%	6	6	N/A	N/A	N/A	N/A	0%	48%	24%	17%	17%	29%	0.97	0.88	1.65
C84	Hexagon	52%	6	6	N/A	N/A	N/A	N/A	0%	36%	18%	20%	20%	22%	0.97	0.88	1.65
C85	Hexagon	22%	6	6	N/A	N/A	N/A	N/A	0%	60%	30%	14%	14%	36%	0.97	0.88	1.65
C91	Hexagon	69%	6	6	N/A	N/A	N/A	N/A	0%	24%	12%	24%	23%	14%	0.97	0.88	1.65
C92	Hexagon	53%	6	6	N/A	N/A	N/A	N/A	0%	36%	18%	21%	20%	22%	0.97	0.88	1.65
C93	Hexagon	37%	6	6	N/A	N/A	N/A	N/A	0%	48%	24%	17%	17%	29%	0.97	0.88	1.65
C94	Hexagon	10%	6	6	N/A	N/A	N/A	N/A	0%	69%	34%	12%	11%	41%	0.97	0.88	1.65
C95	Hexagon	32%	6	6	N/A	N/A	N/A	N/A	0%	52%	26%	16%	16%	31%	0.97	0.88	1.65
C96	Hexagon	47%	6	6	N/A	N/A	N/A	N/A	0%	40%	20%	19%	19%	24%	0.97	0.88	1.65
C101	Parallelogram	63%	6	6	N/A	N/A	N/A	N/A	0%	28%	14%	23%	22%	17%	0.97	0.88	1.65
C102	Parallelogram	30%	6	6	N/A	N/A	N/A	N/A	0%	53%	27%	16%	15%	32%	0.97	0.88	1.65
C103	Parallelogram	37%	6	6	N/A	N/A	N/A	N/A	0%	48%	24%	17%	17%	29%	0.97	0.88	1.65
C104	Parallelogram	32%	6	6	N/A	N/A	N/A	N/A	0%	52%	26%	16%	16%	31%	0.97	0.88	1.65
C105	Parallelogram	23%	6	6	N/A	N/A	N/A	N/A	0%	58%	29%	15%	14%	35%	0.97	0.88	1.65
C106	Parallelogram	50%	6	6	N/A	N/A	N/A	N/A	0%	38%	19%	20%	19%	23%	0.97	0.88	1.65
C111	Parallelogram	53%	6	6	N/A	N/A	N/A	N/A	0%	36%	18%	21%	20%	22%	0.97	0.88	1.65
C112	Parallelogram	40%	6	6	N/A	N/A	N/A	N/A	0%	46%	23%	18%	17%	28%	0.97	0.88	1.65
C113	Parallelogram	43%	6	6	N/A	N/A	N/A	N/A	0%	43%	22%	19%	18%	26%	0.97	0.88	1.65
C114	Parallelogram	27%	6	6	N/A	N/A	N/A	N/A	0%	56%	28%	15%	15%	34%	0.97	0.88	1.65
C115	Parallelogram	40%	6	6	N/A	N/A	N/A	N/A	0%	46%	23%	18%	17%	28%	0.97	0.88	1.65
C116	Parallelogram	27%	6	6	N/A	N/A	N/A	N/A	0%	56%	28%	15%	15%	34%	0.97	0.88	1.65

Panel Layers			Layers							UV %	Visible Light Transmittance	Total Solar Transmittance	Visible Reflectance		Solar Heat Gain Coefficient	U-Value (BTU/hrft2F)		Light to Solar Gain
LowIron-LowIron-Spacer-Clear			Class L1 Thickness	Class L2 Thickness	Spacer Size	Class L3 Thickness	Spacer Size	Class L4 Thickness	Exterior				Interior	Winter Nighttime		Summer Daytime		
Panel Type	Shape	Cell Coverage Area																
C74	Triangle	47%	3	3	12	3	N/A	N/A	0%	43%	37%	22%	22%	40%	0.45	0.47	1.08	
C75	Triangle	37%	3	3	12	3	N/A	N/A	0%	52%	44%	21%	21%	48%	0.45	0.47	1.08	
C76	Triangle	41%	3	3	12	3	N/A	N/A	0%	48%	41%	21%	21%	45%	0.45	0.47	1.08	
C17	Hexagon	48%	3	3	12	3	N/A	N/A	0%	42%	36%	22%	22%	39%	0.45	0.47	1.08	
C18	Hexagon	32%	3	3	12	3	N/A	N/A	0%	56%	47%	20%	20%	52%	0.45	0.47	1.08	
C19	Hexagon	16%	3	3	12	3	N/A	N/A	0%	69%	59%	17%	17%	64%	0.45	0.47	1.08	
C81	Hexagon	68%	3	3	12	3	N/A	N/A	0%	26%	22%	25%	25%	24%	0.45	0.47	1.08	
C82	Hexagon	36%	3	3	12	3	N/A	N/A	0%	52%	44%	20%	20%	48%	0.45	0.47	1.08	
C83	Hexagon	36%	3	3	12	3	N/A	N/A	0%	52%	44%	20%	20%	48%	0.45	0.47	1.08	
C84	Hexagon	52%	3	3	12	3	N/A	N/A	0%	39%	33%	23%	23%	36%	0.45	0.47	1.08	
C85	Hexagon	22%	3	3	12	3	N/A	N/A	0%	64%	55%	18%	18%	60%	0.45	0.47	1.08	
C91	Hexagon	69%	3	3	12	3	N/A	N/A	0%	25%	22%	25%	25%	24%	0.45	0.47	1.08	
C92	Hexagon	53%	3	3	12	3	N/A	N/A	0%	38%	33%	23%	23%	36%	0.45	0.47	1.08	
C93	Hexagon	37%	3	3	12	3	N/A	N/A	0%	51%	44%	21%	21%	48%	0.45	0.47	1.08	
C94	Hexagon	10%	3	3	12	3	N/A	N/A	0%	74%	63%	16%	16%	69%	0.45	0.47	1.08	
C95	Hexagon	32%	3	3	12	3	N/A	N/A	0%	56%	48%	20%	20%	52%	0.45	0.47	1.08	
C96	Hexagon	47%	3	3	12	3	N/A	N/A	0%	43%	37%	22%	22%	40%	0.45	0.47	1.08	
C101	Parallelogram	63%	3	3	12	3	N/A	N/A	0%	30%	26%	24%	24%	28%	0.45	0.47	1.08	
C102	Parallelogram	30%	3	3	12	3	N/A	N/A	0%	57%	49%	19%	19%	53%	0.45	0.47	1.08	
C103	Parallelogram	37%	3	3	12	3	N/A	N/A	0%	52%	44%	20%	20%	48%	0.45	0.47	1.08	
C104	Parallelogram	32%	3	3	12	3	N/A	N/A	0%	56%	48%	20%	20%	52%	0.45	0.47	1.08	
C105	Parallelogram	23%	3	3	12	3	N/A	N/A	0%	63%	54%	18%	18%	58%	0.45	0.47	1.08	
C106	Parallelogram	50%	3	3	12	3	N/A	N/A	0%	41%	35%	22%	22%	38%	0.45	0.47	1.08	
C111	Parallelogram	53%	3	3	12	3	N/A	N/A	0%	38%	33%	23%	23%	36%	0.45	0.47	1.08	
C112	Parallelogram	40%	3	3	12	3	N/A	N/A	0%	49%	42%	21%	21%	46%	0.45	0.47	1.08	
C113	Parallelogram	43%	3	3	12	3	N/A	N/A	0%	47%	40%	21%	21%	43%	0.45	0.47	1.08	
C114	Parallelogram	27%	3	3	12	3	N/A	N/A	0%	60%	51%	19%	19%	56%	0.45	0.47	1.08	
C115	Parallelogram	40%	3	3	12	3	N/A	N/A	0%	49%	42%	21%	21%	46%	0.45	0.47	1.08	
C116	Parallelogram	27%	3	3	12	3	N/A	N/A	0%	60%	51%	19%	19%	56%	0.45	0.47	1.08	

Panel Layers			Layers							UV %	Visible Light Transmittance	Total Solar Transmittance	Visible Reflectance		Solar Heat Gain Coefficient	U-Value (BTU/hrft2F)		Light to Solar Gain
LowIron-LowIron-Spacer-Clear			Class L1	Class L2	Spacer	Class L3	Spacer	Class L4	Exterior				Interior	Winter Nighttime		Summer Daytime		
Panel Type	Shape	Cell Coverage Area	Thickness	Thickness	Size	Thickness	Size	Thickness										
C74	Triangle	47%	4	4	12	4	N/A	N/A	1%	43%	36%	22%	22%	40%	0.44	0.47	1.09	
C75	Triangle	37%	4	4	12	4	N/A	N/A	1%	52%	43%	21%	21%	47%	0.44	0.47	1.09	
C76	Triangle	41%	4	4	12	4	N/A	N/A	1%	48%	40%	21%	21%	44%	0.44	0.47	1.09	
C17	Hexagon	48%	4	4	12	4	N/A	N/A	1%	42%	35%	22%	22%	39%	0.44	0.47	1.09	
C18	Hexagon	32%	4	4	12	4	N/A	N/A	1%	56%	46%	20%	20%	51%	0.44	0.47	1.09	
C19	Hexagon	16%	4	4	12	4	N/A	N/A	1%	69%	57%	17%	17%	63%	0.44	0.47	1.09	
C81	Hexagon	68%	4	4	12	4	N/A	N/A	0%	26%	22%	25%	25%	24%	0.44	0.47	1.09	
C82	Hexagon	36%	4	4	12	4	N/A	N/A	1%	52%	43%	20%	20%	48%	0.44	0.47	1.09	
C83	Hexagon	36%	4	4	12	4	N/A	N/A	1%	52%	43%	20%	20%	48%	0.44	0.47	1.09	
C84	Hexagon	52%	4	4	12	4	N/A	N/A	0%	39%	32%	23%	23%	36%	0.44	0.47	1.09	
C85	Hexagon	22%	4	4	12	4	N/A	N/A	1%	64%	53%	18%	18%	59%	0.44	0.47	1.09	
C91	Hexagon	69%	4	4	12	4	N/A	N/A	0%	25%	21%	25%	25%	23%	0.44	0.47	1.09	
C92	Hexagon	53%	4	4	12	4	N/A	N/A	0%	38%	32%	23%	23%	35%	0.44	0.47	1.09	
C93	Hexagon	37%	4	4	12	4	N/A	N/A	1%	51%	43%	21%	21%	47%	0.44	0.47	1.09	
C94	Hexagon	10%	4	4	12	4	N/A	N/A	1%	74%	61%	16%	16%	68%	0.44	0.47	1.09	
C95	Hexagon	32%	4	4	12	4	N/A	N/A	1%	56%	47%	20%	20%	51%	0.44	0.47	1.09	
C96	Hexagon	47%	4	4	12	4	N/A	N/A	1%	43%	36%	22%	22%	40%	0.44	0.47	1.09	
C101	Parallelogram	63%	4	4	12	4	N/A	N/A	0%	30%	25%	24%	24%	28%	0.44	0.47	1.09	
C102	Parallelogram	30%	4	4	12	4	N/A	N/A	1%	57%	48%	19%	19%	53%	0.44	0.47	1.09	
C103	Parallelogram	37%	4	4	12	4	N/A	N/A	1%	52%	43%	20%	20%	48%	0.44	0.47	1.09	
C104	Parallelogram	32%	4	4	12	4	N/A	N/A	1%	56%	47%	20%	20%	51%	0.44	0.47	1.09	
C105	Parallelogram	23%	4	4	12	4	N/A	N/A	1%	63%	52%	18%	18%	58%	0.44	0.47	1.09	
C106	Parallelogram	50%	4	4	12	4	N/A	N/A	1%	41%	34%	22%	22%	38%	0.44	0.47	1.09	
C111	Parallelogram	53%	4	4	12	4	N/A	N/A	0%	38%	32%	23%	23%	35%	0.44	0.47	1.09	
C112	Parallelogram	40%	4	4	12	4	N/A	N/A	1%	49%	41%	21%	21%	45%	0.44	0.47	1.09	
C113	Parallelogram	43%	4	4	12	4	N/A	N/A	1%	47%	39%	21%	21%	43%	0.44	0.47	1.09	
C114	Parallelogram	27%	4	4	12	4	N/A	N/A	1%	60%	50%	19%	19%	55%	0.44	0.47	1.09	
C115	Parallelogram	40%	4	4	12	4	N/A	N/A	1%	49%	41%	21%	21%	45%	0.44	0.47	1.09	
C116	Parallelogram	27%	4	4	12	4	N/A	N/A	1%	60%	50%	19%	19%	55%	0.44	0.47	1.09	

Panel Layers			Layers						UV %	Visible Light Transmittance	Total Solar Transmittance	Visible Reflectance		Solar Heat Gain Coefficient	U-Value (BTU/hrft2F)		Light to Solar Gain
LowIron-LowIron-Spacer-Clear			Class L1	Class L2	Spacer	Class L3	Spacer	Class L4				Exterior	Interior		Winter Nighttime	Summer Daytime	
Panel Type	Shape	Cell Coverage Area	Thickness	Thickness	Size	Thickness	Size	Thickness									
C74	Triangle	47%	6	6	12	6	N/A	N/A	0%	43%	33%	22%	22%	38%	0.44	0.46	1.11
C75	Triangle	37%	6	6	12	6	N/A	N/A	0%	51%	40%	21%	21%	46%	0.44	0.46	1.11
C76	Triangle	41%	6	6	12	6	N/A	N/A	0%	47%	37%	21%	21%	43%	0.44	0.46	1.11
C17	Hexagon	48%	6	6	12	6	N/A	N/A	0%	42%	33%	22%	22%	38%	0.44	0.46	1.11
C18	Hexagon	32%	6	6	12	6	N/A	N/A	0%	58%	43%	20%	20%	50%	0.44	0.46	1.11
C19	Hexagon	16%	6	6	12	6	N/A	N/A	0%	68%	53%	17%	17%	61%	0.44	0.46	1.11
C81	Hexagon	68%	6	6	12	6	N/A	N/A	0%	26%	20%	25%	25%	23%	0.44	0.46	1.11
C82	Hexagon	36%	6	6	12	6	N/A	N/A	0%	51%	40%	20%	20%	46%	0.44	0.46	1.11
C83	Hexagon	36%	6	6	12	6	N/A	N/A	0%	51%	40%	20%	20%	46%	0.44	0.46	1.11
C84	Hexagon	52%	6	6	12	6	N/A	N/A	0%	39%	30%	23%	23%	35%	0.44	0.46	1.11
C85	Hexagon	22%	6	6	12	6	N/A	N/A	0%	63%	49%	18%	18%	57%	0.44	0.46	1.11
C91	Hexagon	69%	6	6	12	6	N/A	N/A	0%	25%	20%	25%	25%	23%	0.44	0.46	1.11
C92	Hexagon	53%	6	6	12	6	N/A	N/A	0%	38%	29%	23%	23%	34%	0.44	0.46	1.11
C93	Hexagon	37%	6	6	12	6	N/A	N/A	0%	51%	39%	21%	21%	46%	0.44	0.46	1.11
C94	Hexagon	10%	6	6	12	6	N/A	N/A	0%	73%	57%	16%	16%	66%	0.44	0.46	1.11
C95	Hexagon	32%	6	6	12	6	N/A	N/A	0%	55%	43%	20%	20%	50%	0.44	0.46	1.11
C96	Hexagon	47%	6	6	12	6	N/A	N/A	0%	43%	33%	22%	22%	38%	0.44	0.46	1.11
C101	Parallelogram	63%	6	6	12	6	N/A	N/A	0%	30%	23%	24%	24%	27%	0.44	0.46	1.11
C102	Parallelogram	30%	6	6	12	6	N/A	N/A	0%	57%	44%	19%	19%	51%	0.44	0.46	1.11
C103	Parallelogram	37%	6	6	12	6	N/A	N/A	0%	51%	40%	20%	20%	46%	0.44	0.46	1.11
C104	Parallelogram	32%	6	6	12	6	N/A	N/A	0%	55%	43%	20%	20%	50%	0.44	0.46	1.11
C105	Parallelogram	23%	6	6	12	6	N/A	N/A	0%	62%	48%	18%	18%	56%	0.44	0.46	1.11
C106	Parallelogram	50%	6	6	12	6	N/A	N/A	0%	41%	32%	22%	22%	37%	0.44	0.46	1.11
C111	Parallelogram	53%	6	6	12	6	N/A	N/A	0%	38%	29%	23%	23%	34%	0.44	0.46	1.11
C112	Parallelogram	40%	6	6	12	6	N/A	N/A	0%	49%	38%	21%	21%	44%	0.44	0.46	1.11
C113	Parallelogram	43%	6	6	12	6	N/A	N/A	0%	46%	36%	21%	21%	41%	0.44	0.46	1.11
C114	Parallelogram	27%	6	6	12	6	N/A	N/A	0%	59%	46%	19%	19%	54%	0.44	0.46	1.11
C115	Parallelogram	40%	6	6	12	6	N/A	N/A	0%	49%	38%	21%	21%	44%	0.44	0.46	1.11
C116	Parallelogram	27%	6	6	12	6	N/A	N/A	0%	59%	46%	19%	19%	54%	0.44	0.46	1.11

Panel Layers			Layers							UV %	Visible Light Transmittance	Total Solar Transmittance	Visible Reflectance		Solar Heat Gain Coefficient	U-Value (BTU/hrft2F)		Light to Solar Gain
LowIron-LowIron-Spacer-LowIron			Class L1 Thickness	Class L2 Thickness	Spacer Size	Class L3 Thickness	Spacer Size	Class L4 Thickness	Exterior				Interior	Winter Nighttime		Summer Daytime		
Panel Type	Shape	Cell Coverage Area																
C74	Triangle	47%	3	3	12	3	N/A	N/A	0%	44%	40%	22%	22%	41%	0.45	0.47	1.08	
C75	Triangle	37%	3	3	12	3	N/A	N/A	0%	53%	48%	21%	21%	49%	0.45	0.47	1.08	
C76	Triangle	41%	3	3	12	3	N/A	N/A	0%	49%	45%	21%	21%	46%	0.45	0.47	1.08	
C17	Hexagon	48%	3	3	12	3	N/A	N/A	0%	43%	39%	22%	22%	40%	0.45	0.47	1.08	
C18	Hexagon	32%	3	3	12	3	N/A	N/A	0%	57%	52%	20%	20%	53%	0.45	0.47	1.08	
C19	Hexagon	16%	3	3	12	3	N/A	N/A	0%	70%	64%	17%	17%	65%	0.45	0.47	1.08	
C81	Hexagon	68%	3	3	12	3	N/A	N/A	0%	27%	24%	25%	25%	25%	0.45	0.47	1.08	
C82	Hexagon	36%	3	3	12	3	N/A	N/A	0%	53%	48%	20%	20%	50%	0.45	0.47	1.08	
C83	Hexagon	36%	3	3	12	3	N/A	N/A	0%	53%	48%	20%	20%	50%	0.45	0.47	1.08	
C84	Hexagon	52%	3	3	12	3	N/A	N/A	0%	40%	36%	23%	23%	37%	0.45	0.47	1.08	
C85	Hexagon	22%	3	3	12	3	N/A	N/A	0%	66%	60%	18%	18%	61%	0.45	0.47	1.08	
C91	Hexagon	69%	3	3	12	3	N/A	N/A	0%	26%	24%	25%	25%	24%	0.45	0.47	1.08	
C92	Hexagon	53%	3	3	12	3	N/A	N/A	0%	39%	36%	23%	23%	36%	0.45	0.47	1.08	
C93	Hexagon	37%	3	3	12	3	N/A	N/A	0%	53%	48%	21%	21%	49%	0.45	0.47	1.08	
C94	Hexagon	10%	3	3	12	3	N/A	N/A	0%	76%	69%	16%	16%	70%	0.45	0.47	1.08	
C95	Hexagon	32%	3	3	12	3	N/A	N/A	0%	58%	52%	20%	20%	53%	0.45	0.47	1.08	
C96	Hexagon	47%	3	3	12	3	N/A	N/A	0%	44%	40%	22%	22%	41%	0.45	0.47	1.08	
C101	Parallelogram	63%	3	3	12	3	N/A	N/A	0%	31%	28%	24%	24%	29%	0.45	0.47	1.08	
C102	Parallelogram	30%	3	3	12	3	N/A	N/A	0%	59%	53%	19%	19%	55%	0.45	0.47	1.08	
C103	Parallelogram	37%	3	3	12	3	N/A	N/A	0%	53%	48%	20%	20%	49%	0.45	0.47	1.08	
C104	Parallelogram	32%	3	3	12	3	N/A	N/A	0%	57%	52%	20%	20%	53%	0.45	0.47	1.08	
C105	Parallelogram	23%	3	3	12	3	N/A	N/A	0%	64%	58%	18%	18%	60%	0.45	0.47	1.08	
C106	Parallelogram	50%	3	3	12	3	N/A	N/A	0%	42%	38%	22%	22%	39%	0.45	0.47	1.08	
C111	Parallelogram	53%	3	3	12	3	N/A	N/A	0%	39%	36%	23%	23%	36%	0.45	0.47	1.08	
C112	Parallelogram	40%	3	3	12	3	N/A	N/A	0%	50%	46%	21%	21%	47%	0.45	0.47	1.08	
C113	Parallelogram	43%	3	3	12	3	N/A	N/A	0%	48%	43%	21%	21%	44%	0.45	0.47	1.08	
C114	Parallelogram	27%	3	3	12	3	N/A	N/A	0%	62%	56%	19%	19%	57%	0.45	0.47	1.08	
C115	Parallelogram	40%	3	3	12	3	N/A	N/A	0%	50%	46%	21%	21%	47%	0.45	0.47	1.08	
C116	Parallelogram	27%	3	3	12	3	N/A	N/A	0%	62%	56%	19%	19%	57%	0.45	0.47	1.08	

Panel Layers			Layers							UV %	Visible Light Transmittance	Total Solar Transmittance	Visible Reflectance		Solar Heat Gain Coefficient	U-Value (BTU/hrft2F)		Light to Solar Gain
LowIron-LowIron-Spacer-LowIron			Class L1 Thickness	Class L2 Thickness	Spacer Size	Class L3 Thickness	Spacer Size	Class L4 Thickness	Exterior				Interior	Winter Nighttime		Summer Daytime		
Panel Type	Shape	Cell Coverage Area																
C74	Triangle	47%	4	4	12	4	N/A	N/A	1%	44%	40%	22%	22%	41%	0.44	0.47	1.08	
C75	Triangle	37%	4	4	12	4	N/A	N/A	1%	52%	47%	21%	21%	49%	0.44	0.47	1.08	
C76	Triangle	41%	4	4	12	4	N/A	N/A	1%	49%	44%	21%	21%	45%	0.44	0.47	1.08	
C17	Hexagon	48%	4	4	12	4	N/A	N/A	1%	43%	39%	22%	22%	40%	0.44	0.47	1.08	
C18	Hexagon	32%	4	4	12	4	N/A	N/A	1%	56%	51%	20%	20%	52%	0.44	0.47	1.08	
C19	Hexagon	16%	4	4	12	4	N/A	N/A	1%	70%	63%	17%	17%	65%	0.44	0.47	1.08	
C81	Hexagon	68%	4	4	12	4	N/A	N/A	0%	27%	24%	25%	25%	25%	0.44	0.47	1.08	
C82	Hexagon	36%	4	4	12	4	N/A	N/A	1%	53%	48%	20%	20%	49%	0.44	0.47	1.08	
C83	Hexagon	36%	4	4	12	4	N/A	N/A	1%	53%	48%	20%	20%	49%	0.44	0.47	1.08	
C84	Hexagon	52%	4	4	12	4	N/A	N/A	0%	40%	36%	23%	23%	37%	0.44	0.47	1.08	
C85	Hexagon	22%	4	4	12	4	N/A	N/A	1%	65%	59%	18%	18%	60%	0.44	0.47	1.08	
C91	Hexagon	69%	4	4	12	4	N/A	N/A	0%	26%	23%	25%	25%	24%	0.44	0.47	1.08	
C92	Hexagon	53%	4	4	12	4	N/A	N/A	0%	39%	35%	23%	23%	36%	0.44	0.47	1.08	
C93	Hexagon	37%	4	4	12	4	N/A	N/A	1%	52%	47%	21%	21%	48%	0.44	0.47	1.08	
C94	Hexagon	10%	4	4	12	4	N/A	N/A	1%	75%	68%	16%	16%	69%	0.44	0.47	1.08	
C95	Hexagon	32%	4	4	12	4	N/A	N/A	1%	57%	51%	20%	20%	53%	0.44	0.47	1.08	
C96	Hexagon	47%	4	4	12	4	N/A	N/A	1%	44%	40%	22%	22%	41%	0.44	0.47	1.08	
C101	Parallelogram	63%	4	4	12	4	N/A	N/A	0%	31%	28%	24%	24%	28%	0.44	0.47	1.08	
C102	Parallelogram	30%	4	4	12	4	N/A	N/A	1%	58%	53%	19%	19%	54%	0.44	0.47	1.08	
C103	Parallelogram	37%	4	4	12	4	N/A	N/A	1%	53%	48%	20%	20%	49%	0.44	0.47	1.08	
C104	Parallelogram	32%	4	4	12	4	N/A	N/A	1%	57%	51%	20%	20%	53%	0.44	0.47	1.08	
C105	Parallelogram	23%	4	4	12	4	N/A	N/A	1%	64%	58%	18%	18%	59%	0.44	0.47	1.08	
C106	Parallelogram	50%	4	4	12	4	N/A	N/A	1%	42%	38%	22%	22%	39%	0.44	0.47	1.08	
C111	Parallelogram	53%	4	4	12	4	N/A	N/A	0%	39%	35%	23%	23%	36%	0.44	0.47	1.08	
C112	Parallelogram	40%	4	4	12	4	N/A	N/A	1%	50%	45%	21%	21%	46%	0.44	0.47	1.08	
C113	Parallelogram	43%	4	4	12	4	N/A	N/A	1%	47%	43%	21%	21%	44%	0.44	0.47	1.08	
C114	Parallelogram	27%	4	4	12	4	N/A	N/A	1%	61%	55%	19%	19%	57%	0.44	0.47	1.08	
C115	Parallelogram	40%	4	4	12	4	N/A	N/A	1%	50%	45%	21%	21%	46%	0.44	0.47	1.08	
C116	Parallelogram	27%	4	4	12	4	N/A	N/A	1%	61%	55%	19%	19%	57%	0.44	0.47	1.08	

Panel Layers			Layers							UV %	Visible Light Transmittance	Total Solar Transmittance	Visible Reflectance		Solar Heat Gain Coefficient	U-Value (BTU/hrft2F)		Light to Solar Gain
LowIron-LowIron-Spacer-LowIron			Glass L1 Thickness	Glass L2 Thickness	Spacer Size	Glass L3 Thickness	Spacer Size	Glass L4 Thickness	Exterior				Interior	Winter Nighttime		Summer Daytime		
Panel Type	Shape	Cell Coverage Area																
C74	Triangle	47%	6	6	12	6	N/A	N/A	0%	44%	38%	22%	22%	40%	0.44	0.46	1.09	
C75	Triangle	37%	6	6	12	6	N/A	N/A	0%	52%	46%	21%	21%	48%	0.44	0.46	1.09	
C76	Triangle	41%	6	6	12	6	N/A	N/A	0%	49%	43%	21%	21%	45%	0.44	0.46	1.09	
C17	Hexagon	48%	6	6	12	6	N/A	N/A	0%	43%	38%	22%	22%	39%	0.44	0.46	1.09	
C18	Hexagon	32%	6	6	12	6	N/A	N/A	0%	56%	50%	20%	20%	52%	0.44	0.46	1.09	
C19	Hexagon	16%	6	6	12	6	N/A	N/A	0%	70%	61%	17%	17%	64%	0.44	0.46	1.09	
C81	Hexagon	68%	6	6	12	6	N/A	N/A	0%	27%	23%	25%	25%	24%	0.44	0.46	1.09	
C82	Hexagon	36%	6	6	12	6	N/A	N/A	0%	53%	46%	20%	20%	48%	0.44	0.46	1.09	
C83	Hexagon	36%	6	6	12	6	N/A	N/A	0%	53%	46%	20%	20%	48%	0.44	0.46	1.09	
C84	Hexagon	52%	6	6	12	6	N/A	N/A	0%	40%	35%	23%	23%	36%	0.44	0.46	1.09	
C85	Hexagon	22%	6	6	12	6	N/A	N/A	0%	65%	57%	18%	18%	60%	0.44	0.46	1.09	
C91	Hexagon	69%	6	6	12	6	N/A	N/A	0%	26%	23%	25%	25%	24%	0.44	0.46	1.09	
C92	Hexagon	53%	6	6	12	6	N/A	N/A	0%	39%	34%	23%	23%	36%	0.44	0.46	1.09	
C93	Hexagon	37%	6	6	12	6	N/A	N/A	0%	52%	46%	21%	21%	48%	0.44	0.46	1.09	
C94	Hexagon	10%	6	6	12	6	N/A	N/A	0%	75%	66%	16%	16%	69%	0.44	0.46	1.09	
C95	Hexagon	32%	6	6	12	6	N/A	N/A	0%	57%	50%	20%	20%	52%	0.44	0.46	1.09	
C96	Hexagon	47%	6	6	12	6	N/A	N/A	0%	44%	38%	22%	22%	40%	0.44	0.46	1.09	
C101	Parallelogram	63%	6	6	12	6	N/A	N/A	0%	31%	27%	24%	24%	28%	0.44	0.46	1.09	
C102	Parallelogram	30%	6	6	12	6	N/A	N/A	0%	58%	51%	19%	19%	53%	0.44	0.46	1.09	
C103	Parallelogram	37%	6	6	12	6	N/A	N/A	0%	53%	46%	20%	20%	48%	0.44	0.46	1.09	
C104	Parallelogram	32%	6	6	12	6	N/A	N/A	0%	57%	50%	20%	20%	52%	0.44	0.46	1.09	
C105	Parallelogram	23%	6	6	12	6	N/A	N/A	0%	64%	56%	18%	18%	58%	0.44	0.46	1.09	
C106	Parallelogram	50%	6	6	12	6	N/A	N/A	0%	42%	37%	22%	22%	38%	0.44	0.46	1.09	
C111	Parallelogram	53%	6	6	12	6	N/A	N/A	0%	39%	34%	23%	23%	36%	0.44	0.46	1.09	
C112	Parallelogram	40%	6	6	12	6	N/A	N/A	0%	50%	44%	21%	21%	46%	0.44	0.46	1.09	
C113	Parallelogram	43%	6	6	12	6	N/A	N/A	0%	47%	41%	21%	21%	43%	0.44	0.46	1.09	
C114	Parallelogram	27%	6	6	12	6	N/A	N/A	0%	61%	54%	19%	19%	56%	0.44	0.46	1.09	
C115	Parallelogram	40%	6	6	12	6	N/A	N/A	0%	50%	44%	21%	21%	46%	0.44	0.46	1.09	
C116	Parallelogram	27%	6	6	12	6	N/A	N/A	0%	61%	54%	19%	19%	56%	0.44	0.46	1.09	

Panel Layers			Layers						UV %	Visible Light Transmittance	Total Solar Transmittance	Visible Reflectance		Solar Heat Gain Coefficient	U-Value (BTU/hrft2F)		Light to Solar Gain
Panel Type	Shape	Cell Coverage Area	Glass L1 Thickness	Glass L2 Thickness	Spacer Size	Glass L3 Thickness	Spacer Size	Glass L4 Thickness				Exterior	Interior		Winter Nighttime	Summer Daytime	
C74	Triangle	47%	3	3	12	3	N/A	N/A	0%	38%	19%	21%	20%	25%	0.24	0.22	1.52
C75	Triangle	37%	3	3	12	3	N/A	N/A	0%	46%	23%	19%	18%	30%	0.24	0.22	1.52
C76	Triangle	41%	3	3	12	3	N/A	N/A	0%	43%	22%	19%	19%	28%	0.24	0.22	1.52
C17	Hexagon	48%	3	3	12	3	N/A	N/A	0%	38%	19%	21%	20%	25%	0.24	0.22	1.52
C18	Hexagon	32%	3	3	12	3	N/A	N/A	0%	50%	25%	18%	17%	33%	0.24	0.22	1.52
C19	Hexagon	16%	3	3	12	3	N/A	N/A	0%	61%	31%	15%	14%	40%	0.24	0.22	1.52
C81	Hexagon	68%	3	3	12	3	N/A	N/A	0%	23%	12%	24%	24%	15%	0.24	0.22	1.52
C82	Hexagon	36%	3	3	12	3	N/A	N/A	0%	46%	24%	19%	18%	31%	0.24	0.22	1.52
C83	Hexagon	36%	3	3	12	3	N/A	N/A	0%	46%	24%	19%	18%	31%	0.24	0.22	1.52
C84	Hexagon	52%	3	3	12	3	N/A	N/A	0%	35%	18%	21%	21%	23%	0.24	0.22	1.52
C85	Hexagon	22%	3	3	12	3	N/A	N/A	0%	57%	29%	16%	15%	38%	0.24	0.22	1.52
C91	Hexagon	69%	3	3	12	3	N/A	N/A	0%	23%	11%	24%	24%	15%	0.24	0.22	1.52
C92	Hexagon	53%	3	3	12	3	N/A	N/A	0%	34%	17%	22%	21%	22%	0.24	0.22	1.52
C93	Hexagon	37%	3	3	12	3	N/A	N/A	0%	46%	23%	19%	18%	30%	0.24	0.22	1.52
C94	Hexagon	10%	3	3	12	3	N/A	N/A	0%	66%	33%	14%	13%	43%	0.24	0.22	1.52
C95	Hexagon	32%	3	3	12	3	N/A	N/A	0%	50%	25%	18%	17%	33%	0.24	0.22	1.52
C96	Hexagon	47%	3	3	12	3	N/A	N/A	0%	38%	20%	21%	20%	25%	0.24	0.22	1.52
C101	Parallelogram	63%	3	3	12	3	N/A	N/A	0%	27%	14%	23%	23%	18%	0.24	0.22	1.52
C102	Parallelogram	30%	3	3	12	3	N/A	N/A	0%	51%	26%	17%	17%	34%	0.24	0.22	1.52
C103	Parallelogram	37%	3	3	12	3	N/A	N/A	0%	46%	23%	19%	18%	30%	0.24	0.22	1.52
C104	Parallelogram	32%	3	3	12	3	N/A	N/A	0%	50%	25%	18%	17%	33%	0.24	0.22	1.52
C105	Parallelogram	23%	3	3	12	3	N/A	N/A	0%	56%	28%	16%	15%	37%	0.24	0.22	1.52
C106	Parallelogram	50%	3	3	12	3	N/A	N/A	0%	37%	19%	21%	20%	24%	0.24	0.22	1.52
C111	Parallelogram	53%	3	3	12	3	N/A	N/A	0%	34%	17%	22%	21%	22%	0.24	0.22	1.52
C112	Parallelogram	40%	3	3	12	3	N/A	N/A	0%	44%	22%	19%	19%	29%	0.24	0.22	1.52
C113	Parallelogram	43%	3	3	12	3	N/A	N/A	0%	41%	21%	20%	19%	27%	0.24	0.22	1.52
C114	Parallelogram	27%	3	3	12	3	N/A	N/A	0%	54%	27%	17%	16%	35%	0.24	0.22	1.52
C115	Parallelogram	40%	3	3	12	3	N/A	N/A	0%	44%	22%	19%	19%	29%	0.24	0.22	1.52
C116	Parallelogram	27%	3	3	12	3	N/A	N/A	0%	54%	27%	17%	16%	35%	0.24	0.22	1.52

Panel Layers			Layers							UV %	Visible Light Transmittance	Total Solar Transmittance	Visible Reflectance		Solar Heat Gain Coefficient	U-Value (BTU/hrft2F)		Light to Solar Gain
Panel Type	Shape	Cell Coverage Area	Glass L1 Thickness	Glass L2 Thickness	Spacer Size	Glass L3 Thickness	Spacer Size	Glass L4 Thickness	Exterior				Interior	Winter Nighttime		Summer Daytime		
C74	Triangle	47%	4	4	12	4	N/A	N/A	0%	38%	19%	21%	20%	25%	0.24	0.22	1.52	
C75	Triangle	37%	4	4	12	4	N/A	N/A	0%	46%	23%	19%	18%	30%	0.24	0.22	1.52	
C76	Triangle	41%	4	4	12	4	N/A	N/A	0%	43%	21%	19%	19%	28%	0.24	0.22	1.52	
C17	Hexagon	48%	4	4	12	4	N/A	N/A	0%	38%	19%	21%	20%	25%	0.24	0.22	1.52	
C18	Hexagon	32%	4	4	12	4	N/A	N/A	0%	50%	24%	18%	17%	33%	0.24	0.22	1.52	
C19	Hexagon	16%	4	4	12	4	N/A	N/A	0%	61%	30%	15%	14%	40%	0.24	0.22	1.52	
C81	Hexagon	68%	4	4	12	4	N/A	N/A	0%	23%	12%	24%	24%	15%	0.24	0.22	1.52	
C82	Hexagon	36%	4	4	12	4	N/A	N/A	0%	46%	23%	19%	18%	31%	0.24	0.22	1.52	
C83	Hexagon	36%	4	4	12	4	N/A	N/A	0%	46%	23%	19%	18%	31%	0.24	0.22	1.52	
C84	Hexagon	52%	4	4	12	4	N/A	N/A	0%	35%	17%	21%	21%	23%	0.24	0.22	1.52	
C85	Hexagon	22%	4	4	12	4	N/A	N/A	0%	57%	28%	16%	15%	38%	0.24	0.22	1.52	
C91	Hexagon	69%	4	4	12	4	N/A	N/A	0%	23%	11%	24%	24%	15%	0.24	0.22	1.52	
C92	Hexagon	53%	4	4	12	4	N/A	N/A	0%	34%	17%	22%	21%	22%	0.24	0.22	1.52	
C93	Hexagon	37%	4	4	12	4	N/A	N/A	0%	46%	23%	19%	18%	30%	0.24	0.22	1.52	
C94	Hexagon	10%	4	4	12	4	N/A	N/A	0%	66%	32%	14%	13%	43%	0.24	0.22	1.52	
C95	Hexagon	32%	4	4	12	4	N/A	N/A	0%	50%	25%	18%	17%	33%	0.24	0.22	1.52	
C96	Hexagon	47%	4	4	12	4	N/A	N/A	0%	38%	19%	21%	20%	25%	0.24	0.22	1.52	
C101	Parallelogram	63%	4	4	12	4	N/A	N/A	0%	27%	13%	23%	23%	18%	0.24	0.22	1.52	
C102	Parallelogram	30%	4	4	12	4	N/A	N/A	0%	51%	25%	17%	17%	34%	0.24	0.22	1.52	
C103	Parallelogram	37%	4	4	12	4	N/A	N/A	0%	46%	23%	19%	18%	30%	0.24	0.22	1.52	
C104	Parallelogram	32%	4	4	12	4	N/A	N/A	0%	50%	25%	18%	17%	33%	0.24	0.22	1.52	
C105	Parallelogram	23%	4	4	12	4	N/A	N/A	0%	56%	28%	16%	15%	37%	0.24	0.22	1.52	
C106	Parallelogram	50%	4	4	12	4	N/A	N/A	0%	37%	18%	21%	20%	24%	0.24	0.22	1.52	
C111	Parallelogram	53%	4	4	12	4	N/A	N/A	0%	34%	17%	22%	21%	22%	0.24	0.22	1.52	
C112	Parallelogram	40%	4	4	12	4	N/A	N/A	0%	44%	22%	19%	19%	29%	0.24	0.22	1.52	
C113	Parallelogram	43%	4	4	12	4	N/A	N/A	0%	41%	20%	20%	19%	27%	0.24	0.22	1.52	
C114	Parallelogram	27%	4	4	12	4	N/A	N/A	0%	54%	26%	17%	16%	35%	0.24	0.22	1.52	
C115	Parallelogram	40%	4	4	12	4	N/A	N/A	0%	44%	22%	19%	19%	29%	0.24	0.22	1.52	
C116	Parallelogram	27%	4	4	12	4	N/A	N/A	0%	54%	26%	17%	16%	35%	0.24	0.22	1.52	

Panel Layers			Layers						UV %	Visible Light Transmittance	Total Solar Transmittance	Visible Reflectance		Solar Heat Gain Coefficient	U-Value (BTU/hrft2F)		Light to Solar Gain
LowIron-LowIron-Spacer-LowEclear			Class L1	Class L2	Spacer	Class L3	Spacer	Class L4				Exterior	Interior		Winter Nighttime	Summer Daytime	
Panel Type	Shape	Cell Coverage Area	Thickness	Thickness	Size	Thickness	Size	Thickness									
C74	Triangle	47%	6	6	12	6	N/A	N/A	0%	38%	18%	21%	20%	25%	0.24	0.22	1.50
C75	Triangle	37%	6	6	12	6	N/A	N/A	0%	45%	22%	19%	18%	30%	0.24	0.22	1.50
C76	Triangle	41%	6	6	12	6	N/A	N/A	0%	42%	21%	19%	19%	28%	0.24	0.22	1.50
C17	Hexagon	48%	6	6	12	6	N/A	N/A	0%	37%	18%	21%	20%	25%	0.24	0.22	1.50
C18	Hexagon	32%	6	6	12	6	N/A	N/A	0%	49%	24%	18%	17%	33%	0.24	0.22	1.50
C19	Hexagon	16%	6	6	12	6	N/A	N/A	0%	60%	29%	15%	14%	40%	0.24	0.22	1.50
C81	Hexagon	68%	6	6	12	6	N/A	N/A	0%	23%	11%	24%	24%	15%	0.24	0.22	1.50
C82	Hexagon	36%	6	6	12	6	N/A	N/A	0%	46%	22%	19%	18%	31%	0.24	0.22	1.50
C83	Hexagon	36%	6	6	12	6	N/A	N/A	0%	46%	22%	19%	18%	31%	0.24	0.22	1.50
C84	Hexagon	52%	6	6	12	6	N/A	N/A	0%	34%	17%	21%	21%	23%	0.24	0.22	1.50
C85	Hexagon	22%	6	6	12	6	N/A	N/A	0%	56%	27%	16%	15%	38%	0.24	0.22	1.50
C91	Hexagon	69%	6	6	12	6	N/A	N/A	0%	22%	11%	24%	24%	15%	0.24	0.22	1.50
C92	Hexagon	53%	6	6	12	6	N/A	N/A	0%	34%	16%	22%	21%	22%	0.24	0.22	1.50
C93	Hexagon	37%	6	6	12	6	N/A	N/A	0%	45%	22%	19%	18%	30%	0.24	0.22	1.50
C94	Hexagon	10%	6	6	12	6	N/A	N/A	0%	65%	32%	14%	13%	43%	0.24	0.22	1.50
C95	Hexagon	32%	6	6	12	6	N/A	N/A	0%	49%	24%	18%	17%	33%	0.24	0.22	1.50
C96	Hexagon	47%	6	6	12	6	N/A	N/A	0%	38%	18%	21%	20%	25%	0.24	0.22	1.50
C101	Parallelogram	63%	6	6	12	6	N/A	N/A	0%	27%	13%	23%	23%	18%	0.24	0.22	1.50
C102	Parallelogram	30%	6	6	12	6	N/A	N/A	0%	50%	25%	17%	17%	34%	0.24	0.22	1.50
C103	Parallelogram	37%	6	6	12	6	N/A	N/A	0%	46%	22%	19%	18%	30%	0.24	0.22	1.50
C104	Parallelogram	32%	6	6	12	6	N/A	N/A	0%	49%	24%	18%	17%	33%	0.24	0.22	1.50
C105	Parallelogram	23%	6	6	12	6	N/A	N/A	0%	55%	27%	16%	15%	37%	0.24	0.22	1.50
C106	Parallelogram	50%	6	6	12	6	N/A	N/A	0%	36%	18%	21%	20%	24%	0.24	0.22	1.50
C111	Parallelogram	53%	6	6	12	6	N/A	N/A	0%	34%	16%	22%	21%	22%	0.24	0.22	1.50
C112	Parallelogram	40%	6	6	12	6	N/A	N/A	0%	43%	21%	19%	19%	29%	0.24	0.22	1.50
C113	Parallelogram	43%	6	6	12	6	N/A	N/A	0%	41%	20%	20%	19%	27%	0.24	0.22	1.50
C114	Parallelogram	27%	6	6	12	6	N/A	N/A	0%	53%	26%	17%	16%	35%	0.24	0.22	1.50
C115	Parallelogram	40%	6	6	12	6	N/A	N/A	0%	43%	21%	19%	19%	29%	0.24	0.22	1.50
C116	Parallelogram	27%	6	6	12	6	N/A	N/A	0%	53%	26%	17%	16%	35%	0.24	0.22	1.50

Panel Layers			Layers							UV %	Visible Light Transmittance	Total Solar Transmittance	Visible Reflectance		Solar Heat Gain Coefficient	U-Value (BTU/hrft2F)		Light to Solar Gain
Panel Type	Shape	Cell Coverage Area	Glass L1 Thickness	Glass L2 Thickness	Spacer Size	Glass L3 Thickness	Spacer Size	Glass L4 Thickness	Exterior				Interior	Winter Nighttime		Summer Daytime		
C74	Triangle	47%	3	3	12	3	N/A	N/A	0%	40%	20%	21%	20%	25%	0.29	0.27	1.56	
C75	Triangle	37%	3	3	12	3	N/A	N/A	0%	47%	24%	19%	18%	30%	0.29	0.27	1.56	
C76	Triangle	41%	3	3	12	3	N/A	N/A	0%	44%	22%	19%	19%	28%	0.29	0.27	1.56	
C17	Hexagon	48%	3	3	12	3	N/A	N/A	0%	39%	20%	21%	20%	25%	0.29	0.27	1.56	
C18	Hexagon	32%	3	3	12	3	N/A	N/A	0%	51%	26%	18%	17%	33%	0.29	0.27	1.56	
C19	Hexagon	16%	3	3	12	3	N/A	N/A	0%	63%	32%	15%	14%	40%	0.29	0.27	1.56	
C81	Hexagon	68%	3	3	12	3	N/A	N/A	0%	24%	12%	24%	24%	15%	0.29	0.27	1.56	
C82	Hexagon	36%	3	3	12	3	N/A	N/A	0%	48%	24%	19%	18%	31%	0.29	0.27	1.56	
C83	Hexagon	36%	3	3	12	3	N/A	N/A	0%	48%	24%	19%	18%	31%	0.29	0.27	1.56	
C84	Hexagon	52%	3	3	12	3	N/A	N/A	0%	36%	18%	21%	21%	23%	0.29	0.27	1.56	
C85	Hexagon	22%	3	3	12	3	N/A	N/A	0%	59%	30%	16%	15%	38%	0.29	0.27	1.56	
C91	Hexagon	69%	3	3	12	3	N/A	N/A	0%	23%	12%	24%	24%	15%	0.29	0.27	1.56	
C92	Hexagon	53%	3	3	12	3	N/A	N/A	0%	35%	18%	22%	21%	22%	0.29	0.27	1.56	
C93	Hexagon	37%	3	3	12	3	N/A	N/A	0%	47%	24%	19%	18%	30%	0.29	0.27	1.56	
C94	Hexagon	10%	3	3	12	3	N/A	N/A	0%	68%	34%	14%	13%	43%	0.29	0.27	1.56	
C95	Hexagon	32%	3	3	12	3	N/A	N/A	0%	51%	26%	18%	17%	33%	0.29	0.27	1.56	
C96	Hexagon	47%	3	3	12	3	N/A	N/A	0%	40%	20%	21%	20%	25%	0.29	0.27	1.56	
C101	Parallelogram	63%	3	3	12	3	N/A	N/A	0%	28%	14%	23%	23%	18%	0.29	0.27	1.56	
C102	Parallelogram	30%	3	3	12	3	N/A	N/A	0%	53%	27%	17%	17%	34%	0.29	0.27	1.56	
C103	Parallelogram	37%	3	3	12	3	N/A	N/A	0%	48%	24%	19%	18%	30%	0.29	0.27	1.56	
C104	Parallelogram	32%	3	3	12	3	N/A	N/A	0%	51%	26%	18%	17%	33%	0.29	0.27	1.56	
C105	Parallelogram	23%	3	3	12	3	N/A	N/A	0%	58%	29%	16%	15%	37%	0.29	0.27	1.56	
C106	Parallelogram	50%	3	3	12	3	N/A	N/A	0%	38%	19%	21%	20%	24%	0.29	0.27	1.56	
C111	Parallelogram	53%	3	3	12	3	N/A	N/A	0%	35%	18%	22%	21%	22%	0.29	0.27	1.56	
C112	Parallelogram	40%	3	3	12	3	N/A	N/A	0%	45%	23%	19%	19%	29%	0.29	0.27	1.56	
C113	Parallelogram	43%	3	3	12	3	N/A	N/A	0%	43%	22%	20%	19%	27%	0.29	0.27	1.56	
C114	Parallelogram	27%	3	3	12	3	N/A	N/A	0%	55%	28%	17%	16%	35%	0.29	0.27	1.56	
C115	Parallelogram	40%	3	3	12	3	N/A	N/A	0%	45%	23%	19%	19%	29%	0.29	0.27	1.56	
C116	Parallelogram	27%	3	3	12	3	N/A	N/A	0%	55%	28%	17%	16%	35%	0.29	0.27	1.56	

Panel Layers			Layers							UV %	Visible Light Transmittance	Total Solar Transmittance	Visible Reflectance		Solar Heat Gain Coefficient	U-Value (BTU/hrft ² F)		Light to Solar Gain
Panel Type	Shape	Cell Coverage Area	Glass L1 Thickness	Glass L2 Thickness	Spacer Size	Glass L3 Thickness	Spacer Size	Glass L4 Thickness	Exterior				Interior	Winter Nighttime		Summer Daytime		
C74	Triangle	47%	4	4	12	4	N/A	N/A	0%	40%	20%	21%	20%	25%	0.28	0.26	1.56	
C75	Triangle	37%	4	4	12	4	N/A	N/A	0%	47%	24%	19%	18%	30%	0.28	0.26	1.56	
C76	Triangle	41%	4	4	12	4	N/A	N/A	0%	44%	22%	19%	19%	28%	0.28	0.26	1.56	
C17	Hexagon	48%	4	4	12	4	N/A	N/A	0%	39%	20%	21%	20%	25%	0.28	0.26	1.56	
C18	Hexagon	32%	4	4	12	4	N/A	N/A	0%	51%	26%	18%	17%	33%	0.28	0.26	1.56	
C19	Hexagon	16%	4	4	12	4	N/A	N/A	0%	63%	32%	15%	14%	40%	0.28	0.26	1.56	
C81	Hexagon	68%	4	4	12	4	N/A	N/A	0%	24%	12%	24%	24%	15%	0.28	0.26	1.56	
C82	Hexagon	36%	4	4	12	4	N/A	N/A	0%	48%	24%	19%	18%	31%	0.28	0.26	1.56	
C83	Hexagon	36%	4	4	12	4	N/A	N/A	0%	48%	24%	19%	18%	31%	0.28	0.26	1.56	
C84	Hexagon	52%	4	4	12	4	N/A	N/A	0%	36%	18%	21%	21%	23%	0.28	0.26	1.56	
C85	Hexagon	22%	4	4	12	4	N/A	N/A	0%	59%	30%	16%	15%	38%	0.28	0.26	1.56	
C91	Hexagon	69%	4	4	12	4	N/A	N/A	0%	23%	12%	24%	24%	15%	0.28	0.26	1.56	
C92	Hexagon	53%	4	4	12	4	N/A	N/A	0%	35%	18%	22%	21%	22%	0.28	0.26	1.56	
C93	Hexagon	37%	4	4	12	4	N/A	N/A	0%	47%	24%	19%	18%	30%	0.28	0.26	1.56	
C94	Hexagon	10%	4	4	12	4	N/A	N/A	0%	68%	34%	14%	13%	43%	0.28	0.26	1.56	
C95	Hexagon	32%	4	4	12	4	N/A	N/A	0%	51%	26%	18%	17%	33%	0.28	0.26	1.56	
C96	Hexagon	47%	4	4	12	4	N/A	N/A	0%	40%	20%	21%	20%	25%	0.28	0.26	1.56	
C101	Parallelogram	63%	4	4	12	4	N/A	N/A	0%	28%	14%	23%	23%	18%	0.28	0.26	1.56	
C102	Parallelogram	30%	4	4	12	4	N/A	N/A	0%	53%	27%	17%	17%	34%	0.28	0.26	1.56	
C103	Parallelogram	37%	4	4	12	4	N/A	N/A	0%	48%	24%	19%	18%	30%	0.28	0.26	1.56	
C104	Parallelogram	32%	4	4	12	4	N/A	N/A	0%	51%	26%	18%	17%	33%	0.28	0.26	1.56	
C105	Parallelogram	23%	4	4	12	4	N/A	N/A	0%	58%	29%	16%	15%	37%	0.28	0.26	1.56	
C106	Parallelogram	50%	4	4	12	4	N/A	N/A	0%	38%	19%	21%	20%	24%	0.28	0.26	1.56	
C111	Parallelogram	53%	4	4	12	4	N/A	N/A	0%	35%	18%	22%	21%	22%	0.28	0.26	1.56	
C112	Parallelogram	40%	4	4	12	4	N/A	N/A	0%	45%	23%	19%	19%	29%	0.28	0.26	1.56	
C113	Parallelogram	43%	4	4	12	4	N/A	N/A	0%	43%	22%	20%	19%	27%	0.28	0.26	1.56	
C114	Parallelogram	27%	4	4	12	4	N/A	N/A	0%	55%	28%	17%	16%	35%	0.28	0.26	1.56	
C115	Parallelogram	40%	4	4	12	4	N/A	N/A	0%	45%	23%	19%	19%	29%	0.28	0.26	1.56	
C116	Parallelogram	27%	4	4	12	4	N/A	N/A	0%	55%	28%	17%	16%	35%	0.28	0.26	1.56	

Panel Layers			Layers							UV %	Visible Light Transmittance	Total Solar Transmittance	Visible Reflectance		Solar Heat Gain Coefficient	U-Value (BTU/hrft2F)		Light to Solar Gain
Panel Type	Shape	Cell Coverage Area	Class L1 Thickness	Class L2 Thickness	Spacer Size	Class L3 Thickness	Spacer Size	Class L4 Thickness	Exterior				Interior	Winter Nighttime		Summer Daytime		
C74	Triangle	47%	6	6	12	6	N/A	N/A	0%	39%	20%	21%	20%	25%	0.24	0.22	1.54	
C75	Triangle	37%	6	6	12	6	N/A	N/A	0%	47%	24%	19%	18%	30%	0.24	0.22	1.54	
C76	Triangle	41%	6	6	12	6	N/A	N/A	0%	43%	22%	19%	19%	28%	0.24	0.22	1.54	
C17	Hexagon	48%	6	6	12	6	N/A	N/A	0%	38%	20%	21%	20%	25%	0.24	0.22	1.54	
C18	Hexagon	32%	6	6	12	6	N/A	N/A	0%	50%	26%	18%	17%	33%	0.24	0.22	1.54	
C19	Hexagon	16%	6	6	12	6	N/A	N/A	0%	62%	32%	15%	14%	40%	0.24	0.22	1.54	
C81	Hexagon	68%	6	6	12	6	N/A	N/A	0%	24%	12%	24%	24%	15%	0.24	0.22	1.54	
C82	Hexagon	36%	6	6	12	6	N/A	N/A	0%	47%	24%	19%	18%	31%	0.24	0.22	1.54	
C83	Hexagon	36%	6	6	12	6	N/A	N/A	0%	47%	24%	19%	18%	31%	0.24	0.22	1.54	
C84	Hexagon	52%	6	6	12	6	N/A	N/A	0%	35%	18%	21%	21%	23%	0.24	0.22	1.54	
C85	Hexagon	22%	6	6	12	6	N/A	N/A	0%	58%	30%	16%	15%	38%	0.24	0.22	1.54	
C91	Hexagon	69%	6	6	12	6	N/A	N/A	0%	23%	12%	24%	24%	15%	0.24	0.22	1.54	
C92	Hexagon	53%	6	6	12	6	N/A	N/A	0%	35%	18%	22%	21%	22%	0.24	0.22	1.54	
C93	Hexagon	37%	6	6	12	6	N/A	N/A	0%	46%	24%	19%	18%	30%	0.24	0.22	1.54	
C94	Hexagon	10%	6	6	12	6	N/A	N/A	0%	67%	34%	14%	13%	43%	0.24	0.22	1.54	
C95	Hexagon	32%	6	6	12	6	N/A	N/A	0%	51%	26%	18%	17%	33%	0.24	0.22	1.54	
C96	Hexagon	47%	6	6	12	6	N/A	N/A	0%	39%	20%	21%	20%	25%	0.24	0.22	1.54	
C101	Parallelogram	63%	6	6	12	6	N/A	N/A	0%	27%	14%	23%	23%	18%	0.24	0.22	1.54	
C102	Parallelogram	30%	6	6	12	6	N/A	N/A	0%	52%	27%	17%	17%	34%	0.24	0.22	1.54	
C103	Parallelogram	37%	6	6	12	6	N/A	N/A	0%	47%	24%	19%	18%	30%	0.24	0.22	1.54	
C104	Parallelogram	32%	6	6	12	6	N/A	N/A	0%	51%	26%	18%	17%	33%	0.24	0.22	1.54	
C105	Parallelogram	23%	6	6	12	6	N/A	N/A	0%	57%	29%	16%	15%	37%	0.24	0.22	1.54	
C106	Parallelogram	50%	6	6	12	6	N/A	N/A	0%	37%	19%	21%	20%	24%	0.24	0.22	1.54	
C111	Parallelogram	53%	6	6	12	6	N/A	N/A	0%	35%	18%	22%	21%	22%	0.24	0.22	1.54	
C112	Parallelogram	40%	6	6	12	6	N/A	N/A	0%	44%	23%	19%	19%	29%	0.24	0.22	1.54	
C113	Parallelogram	43%	6	6	12	6	N/A	N/A	0%	42%	22%	20%	19%	27%	0.24	0.22	1.54	
C114	Parallelogram	27%	6	6	12	6	N/A	N/A	0%	54%	28%	17%	16%	35%	0.24	0.22	1.54	
C115	Parallelogram	40%	6	6	12	6	N/A	N/A	0%	44%	23%	19%	19%	29%	0.24	0.22	1.54	
C116	Parallelogram	27%	6	6	12	6	N/A	N/A	0%	54%	28%	17%	16%	35%	0.24	0.22	1.54	

Panel Layers			Layers						UV %	Visible Light Transmittance	Total Solar Transmittance	Visible Reflectance		Solar Heat Gain Coefficient	U-Value (BTU/hrft2F)		Light to Solar Gain
LowIron-LowIron-Spacer-Clear-Spacer-Clear			Glass L1 Thickness	Glass L2 Thickness	Spacer Size	Glass L3 Thickness	Spacer Size	Glass L4 Thickness				Exterior	Interior		Winter Nighttime	Summer Daytime	
Panel Type	Shape	Cell Coverage Area															
C74	Triangle	47%	3	3	12	3	12	3	0%	40%	31%	25%	25%	36%	0.29	0.32	1.10
C75	Triangle	37%	3	3	12	3	12	3	0%	47%	37%	24%	24%	43%	0.29	0.32	1.10
C76	Triangle	41%	3	3	12	3	12	3	0%	44%	35%	25%	25%	40%	0.29	0.32	1.10
C17	Hexagon	48%	3	3	12	3	12	3	0%	39%	31%	25%	25%	35%	0.29	0.32	1.10
C18	Hexagon	32%	3	3	12	3	12	3	0%	51%	40%	24%	24%	46%	0.29	0.32	1.10
C19	Hexagon	16%	3	3	12	3	12	3	0%	63%	50%	22%	22%	57%	0.29	0.32	1.10
C81	Hexagon	68%	3	3	12	3	12	3	0%	24%	19%	27%	27%	22%	0.29	0.32	1.10
C82	Hexagon	36%	3	3	12	3	12	3	0%	48%	37%	24%	24%	43%	0.29	0.32	1.10
C83	Hexagon	36%	3	3	12	3	12	3	0%	48%	37%	24%	24%	43%	0.29	0.32	1.10
C84	Hexagon	52%	3	3	12	3	12	3	0%	36%	28%	26%	26%	32%	0.29	0.32	1.10
C85	Hexagon	22%	3	3	12	3	12	3	0%	59%	46%	23%	23%	53%	0.29	0.32	1.10
C91	Hexagon	69%	3	3	12	3	12	3	0%	23%	18%	27%	27%	21%	0.29	0.32	1.10
C92	Hexagon	53%	3	3	12	3	12	3	0%	35%	28%	26%	26%	32%	0.29	0.32	1.10
C93	Hexagon	37%	3	3	12	3	12	3	0%	47%	37%	24%	24%	43%	0.29	0.32	1.10
C94	Hexagon	10%	3	3	12	3	12	3	0%	68%	53%	22%	22%	61%	0.29	0.32	1.10
C95	Hexagon	32%	3	3	12	3	12	3	0%	51%	40%	24%	24%	47%	0.29	0.32	1.10
C96	Hexagon	47%	3	3	12	3	12	3	0%	40%	31%	25%	25%	36%	0.29	0.32	1.10
C101	Parallelogram	63%	3	3	12	3	12	3	0%	28%	22%	27%	27%	25%	0.29	0.32	1.10
C102	Parallelogram	30%	3	3	12	3	12	3	0%	53%	41%	24%	24%	48%	0.29	0.32	1.10
C103	Parallelogram	37%	3	3	12	3	12	3	0%	48%	37%	24%	24%	43%	0.29	0.32	1.10
C104	Parallelogram	32%	3	3	12	3	12	3	0%	51%	40%	24%	24%	47%	0.29	0.32	1.10
C105	Parallelogram	23%	3	3	12	3	12	3	0%	58%	45%	23%	23%	52%	0.29	0.32	1.10
C106	Parallelogram	50%	3	3	12	3	12	3	0%	38%	30%	25%	25%	34%	0.29	0.32	1.10
C111	Parallelogram	53%	3	3	12	3	12	3	0%	35%	28%	26%	26%	32%	0.29	0.32	1.10
C112	Parallelogram	40%	3	3	12	3	12	3	0%	45%	35%	25%	25%	41%	0.29	0.32	1.10
C113	Parallelogram	43%	3	3	12	3	12	3	0%	43%	33%	25%	25%	39%	0.29	0.32	1.10
C114	Parallelogram	27%	3	3	12	3	12	3	0%	55%	43%	23%	23%	50%	0.29	0.32	1.10
C115	Parallelogram	40%	3	3	12	3	12	3	0%	45%	35%	25%	25%	41%	0.29	0.32	1.10
C116	Parallelogram	27%	3	3	12	3	12	3	0%	55%	43%	23%	23%	50%	0.29	0.32	1.10

Panel Layers			Layers						UV %	Visible Light Transmittance	Total Solar Transmittance	Visible Reflectance		Solar Heat Gain Coefficient	U-Value (BTU/hrft2F)		Light to Solar Gain
LowIron-LowIron-Spacer-Clear-Spacer-Clear			Glass L1 Thickness	Glass L2 Thickness	Spacer Size	Glass L3 Thickness	Spacer Size	Glass L4 Thickness				Exterior	Interior		Winter Nighttime	Summer Daytime	
Panel Type	Shape	Cell Coverage Area															
C74	Triangle	47%	4	4	12	4	12	4	1%	39%	30%	25%	25%	35%	0.28	0.32	1.10
C75	Triangle	37%	4	4	12	4	12	4	1%	47%	35%	24%	24%	42%	0.28	0.32	1.10
C76	Triangle	41%	4	4	12	4	12	4	1%	43%	33%	25%	25%	39%	0.28	0.32	1.10
C17	Hexagon	48%	4	4	12	4	12	4	1%	38%	29%	25%	25%	35%	0.28	0.32	1.10
C18	Hexagon	32%	4	4	12	4	12	4	1%	50%	38%	24%	24%	45%	0.28	0.32	1.10
C19	Hexagon	16%	4	4	12	4	12	4	1%	62%	47%	22%	22%	56%	0.28	0.32	1.10
C81	Hexagon	68%	4	4	12	4	12	4	0%	24%	18%	27%	27%	21%	0.28	0.32	1.10
C82	Hexagon	36%	4	4	12	4	12	4	1%	47%	36%	24%	24%	43%	0.28	0.32	1.10
C83	Hexagon	36%	4	4	12	4	12	4	1%	47%	36%	24%	24%	43%	0.28	0.32	1.10
C84	Hexagon	52%	4	4	12	4	12	4	0%	35%	27%	26%	26%	32%	0.28	0.32	1.10
C85	Hexagon	22%	4	4	12	4	12	4	1%	58%	44%	23%	23%	52%	0.28	0.32	1.10
C91	Hexagon	69%	4	4	12	4	12	4	0%	23%	17%	27%	27%	21%	0.28	0.32	1.10
C92	Hexagon	53%	4	4	12	4	12	4	0%	35%	26%	26%	26%	31%	0.28	0.32	1.10
C93	Hexagon	37%	4	4	12	4	12	4	1%	46%	35%	24%	24%	42%	0.28	0.32	1.10
C94	Hexagon	10%	4	4	12	4	12	4	1%	67%	50%	22%	22%	60%	0.28	0.32	1.10
C95	Hexagon	32%	4	4	12	4	12	4	1%	51%	38%	24%	24%	46%	0.28	0.32	1.10
C96	Hexagon	47%	4	4	12	4	12	4	1%	39%	30%	25%	25%	35%	0.28	0.32	1.10
C101	Parallelogram	63%	4	4	12	4	12	4	0%	27%	21%	27%	27%	25%	0.28	0.32	1.10
C102	Parallelogram	30%	4	4	12	4	12	4	1%	52%	39%	24%	24%	47%	0.28	0.32	1.10
C103	Parallelogram	37%	4	4	12	4	12	4	1%	47%	36%	24%	24%	42%	0.28	0.32	1.10
C104	Parallelogram	32%	4	4	12	4	12	4	1%	51%	38%	24%	24%	46%	0.28	0.32	1.10
C105	Parallelogram	23%	4	4	12	4	12	4	1%	57%	43%	23%	23%	51%	0.28	0.32	1.10
C106	Parallelogram	50%	4	4	12	4	12	4	1%	37%	28%	25%	25%	34%	0.28	0.32	1.10
C111	Parallelogram	53%	4	4	12	4	12	4	0%	35%	26%	26%	26%	31%	0.28	0.32	1.10
C112	Parallelogram	40%	4	4	12	4	12	4	1%	44%	34%	25%	25%	40%	0.28	0.32	1.10
C113	Parallelogram	43%	4	4	12	4	12	4	1%	42%	32%	25%	25%	38%	0.28	0.32	1.10
C114	Parallelogram	27%	4	4	12	4	12	4	1%	54%	41%	23%	23%	49%	0.28	0.32	1.10
C115	Parallelogram	40%	4	4	12	4	12	4	1%	44%	34%	25%	25%	40%	0.28	0.32	1.10
C116	Parallelogram	27%	4	4	12	4	12	4	1%	54%	41%	23%	23%	49%	0.28	0.32	1.10

Panel Layers			Layers							UV %	Visible Light Transmittance	Total Solar Transmittance	Visible Reflectance		Solar Heat Gain Coefficient	U-Value (BTU/hrft2F)		Light to Solar Gain
Panel Type	Shape	Cell Coverage Area	Class L1 Thickness	Class L2 Thickness	Spacer Size	Class L3 Thickness	Spacer Size	Class L4 Thickness	Exterior				Interior	Winter Nighttime		Summer Daytime		
C74	Triangle	47%	6	6	12	6	12	6	0%	38%	26%	25%	25%	34%	0.28	0.32	1.13	
C75	Triangle	37%	6	6	12	6	12	6	0%	45%	32%	24%	24%	40%	0.28	0.32	1.13	
C76	Triangle	41%	6	6	12	6	12	6	0%	42%	29%	25%	24%	38%	0.28	0.32	1.13	
C17	Hexagon	48%	6	6	12	6	12	6	0%	37%	26%	25%	25%	33%	0.28	0.32	1.13	
C18	Hexagon	32%	6	6	12	6	12	6	0%	49%	34%	24%	23%	43%	0.28	0.32	1.13	
C19	Hexagon	16%	6	6	12	6	12	6	0%	60%	42%	22%	22%	54%	0.28	0.32	1.13	
C81	Hexagon	68%	6	6	12	6	12	6	0%	23%	16%	27%	27%	20%	0.28	0.32	1.13	
C82	Hexagon	36%	6	6	12	6	12	6	0%	46%	32%	24%	24%	41%	0.28	0.32	1.13	
C83	Hexagon	36%	6	6	12	6	12	6	0%	46%	32%	24%	24%	41%	0.28	0.32	1.13	
C84	Hexagon	52%	6	6	12	6	12	6	0%	34%	24%	26%	25%	31%	0.28	0.32	1.13	
C85	Hexagon	22%	6	6	12	6	12	6	0%	56%	39%	23%	22%	50%	0.28	0.32	1.13	
C91	Hexagon	69%	6	6	12	6	12	6	0%	22%	16%	27%	27%	20%	0.28	0.32	1.13	
C92	Hexagon	53%	6	6	12	6	12	6	0%	34%	23%	26%	25%	30%	0.28	0.32	1.13	
C93	Hexagon	37%	6	6	12	6	12	6	0%	45%	31%	24%	24%	40%	0.28	0.32	1.13	
C94	Hexagon	10%	6	6	12	6	12	6	0%	65%	45%	22%	21%	58%	0.28	0.32	1.13	
C95	Hexagon	32%	6	6	12	6	12	6	0%	49%	34%	24%	23%	44%	0.28	0.32	1.13	
C96	Hexagon	47%	6	6	12	6	12	6	0%	38%	26%	25%	25%	34%	0.28	0.32	1.13	
C101	Parallelogram	63%	6	6	12	6	12	6	0%	27%	18%	27%	26%	24%	0.28	0.32	1.13	
C102	Parallelogram	30%	6	6	12	6	12	6	0%	50%	35%	24%	23%	45%	0.28	0.32	1.13	
C103	Parallelogram	37%	6	6	12	6	12	6	0%	46%	32%	24%	24%	41%	0.28	0.32	1.13	
C104	Parallelogram	32%	6	6	12	6	12	6	0%	49%	34%	24%	23%	44%	0.28	0.32	1.13	
C105	Parallelogram	23%	6	6	12	6	12	6	0%	55%	38%	23%	22%	49%	0.28	0.32	1.13	
C106	Parallelogram	50%	6	6	12	6	12	6	0%	36%	25%	25%	25%	32%	0.28	0.32	1.13	
C111	Parallelogram	53%	6	6	12	6	12	6	0%	34%	23%	26%	25%	30%	0.28	0.32	1.13	
C112	Parallelogram	40%	6	6	12	6	12	6	0%	43%	30%	25%	24%	38%	0.28	0.32	1.13	
C113	Parallelogram	43%	6	6	12	6	12	6	0%	41%	28%	25%	24%	36%	0.28	0.32	1.13	
C114	Parallelogram	27%	6	6	12	6	12	6	0%	53%	37%	23%	23%	47%	0.28	0.32	1.13	
C115	Parallelogram	40%	6	6	12	6	12	6	0%	43%	30%	25%	24%	38%	0.28	0.32	1.13	
C116	Parallelogram	27%	6	6	12	6	12	6	0%	53%	37%	23%	23%	47%	0.28	0.32	1.13	

Panel Layers			Layers						UV %	Visible Light Transmittance	Total Solar Transmittance	Visible Reflectance		Solar Heat Gain Coefficient	U-Value (BTU/hrft2F)		Light to Solar Gain
Panel Type	Shape	Cell Coverage Area	Class L1 Thickness	Class L2 Thickness	Spacer Size	Class L3 Thickness	Spacer Size	Class L4 Thickness				Exterior	Interior		Winter Nighttime	Summer Daytime	
C74	Triangle	47%	3	3	12	3	12	3	0%	41%	36%	25%	25%	38%	0.29	0.32	1.07
C75	Triangle	37%	3	3	12	3	12	3	0%	49%	44%	24%	24%	45%	0.29	0.32	1.07
C76	Triangle	41%	3	3	12	3	12	3	0%	45%	40%	25%	25%	42%	0.29	0.32	1.07
C17	Hexagon	48%	3	3	12	3	12	3	0%	40%	36%	25%	25%	37%	0.29	0.32	1.07
C18	Hexagon	32%	3	3	12	3	12	3	0%	52%	47%	24%	24%	49%	0.29	0.32	1.07
C19	Hexagon	16%	3	3	12	3	12	3	0%	65%	58%	22%	22%	60%	0.29	0.32	1.07
C81	Hexagon	68%	3	3	12	3	12	3	0%	25%	22%	27%	27%	23%	0.29	0.32	1.07
C82	Hexagon	36%	3	3	12	3	12	3	0%	49%	44%	24%	24%	46%	0.29	0.32	1.07
C83	Hexagon	36%	3	3	12	3	12	3	0%	49%	44%	24%	24%	46%	0.29	0.32	1.07
C84	Hexagon	52%	3	3	12	3	12	3	0%	37%	33%	26%	26%	34%	0.29	0.32	1.07
C85	Hexagon	22%	3	3	12	3	12	3	0%	60%	54%	23%	23%	56%	0.29	0.32	1.07
C91	Hexagon	69%	3	3	12	3	12	3	0%	24%	21%	27%	27%	22%	0.29	0.32	1.07
C92	Hexagon	53%	3	3	12	3	12	3	0%	36%	32%	26%	26%	34%	0.29	0.32	1.07
C93	Hexagon	37%	3	3	12	3	12	3	0%	48%	43%	24%	24%	45%	0.29	0.32	1.07
C94	Hexagon	10%	3	3	12	3	12	3	0%	69%	62%	22%	22%	65%	0.29	0.32	1.07
C95	Hexagon	32%	3	3	12	3	12	3	0%	53%	47%	24%	24%	49%	0.29	0.32	1.07
C96	Hexagon	47%	3	3	12	3	12	3	0%	41%	36%	25%	25%	38%	0.29	0.32	1.07
C101	Parallelogram	63%	3	3	12	3	12	3	0%	28%	25%	27%	27%	27%	0.29	0.32	1.07
C102	Parallelogram	30%	3	3	12	3	12	3	0%	54%	48%	24%	24%	50%	0.29	0.32	1.07
C103	Parallelogram	37%	3	3	12	3	12	3	0%	49%	44%	24%	24%	46%	0.29	0.32	1.07
C104	Parallelogram	32%	3	3	12	3	12	3	0%	53%	47%	24%	24%	49%	0.29	0.32	1.07
C105	Parallelogram	23%	3	3	12	3	12	3	0%	59%	53%	23%	23%	55%	0.29	0.32	1.07
C106	Parallelogram	50%	3	3	12	3	12	3	0%	39%	35%	25%	25%	36%	0.29	0.32	1.07
C111	Parallelogram	53%	3	3	12	3	12	3	0%	36%	32%	26%	26%	34%	0.29	0.32	1.07
C112	Parallelogram	40%	3	3	12	3	12	3	0%	46%	41%	25%	25%	43%	0.29	0.32	1.07
C113	Parallelogram	43%	3	3	12	3	12	3	0%	44%	39%	25%	25%	41%	0.29	0.32	1.07
C114	Parallelogram	27%	3	3	12	3	12	3	0%	57%	51%	23%	23%	53%	0.29	0.32	1.07
C115	Parallelogram	40%	3	3	12	3	12	3	0%	46%	41%	25%	25%	43%	0.29	0.32	1.07
C116	Parallelogram	27%	3	3	12	3	12	3	0%	57%	51%	23%	23%	53%	0.29	0.32	1.07

Panel Layers			Layers						UV %	Visible Light Transmittance	Total Solar Transmittance	Visible Reflectance		Solar Heat Gain Coefficient	U-Value (BTU/hrft2F)		Light to Solar Gain
Panel Type	Shape	Cell Coverage Area	Class L1 Thickness	Class L2 Thickness	Spacer Size	Class L3 Thickness	Spacer Size	Class L4 Thickness				Exterior	Interior		Winter Nighttime	Summer Daytime	
C74	Triangle	47%	4	4	12	4	12	4	1%	41%	36%	25%	25%	37%	0.28	0.32	1.08
C75	Triangle	37%	4	4	12	4	12	4	1%	49%	43%	24%	24%	45%	0.28	0.32	1.08
C76	Triangle	41%	4	4	12	4	12	4	1%	45%	40%	25%	25%	42%	0.28	0.32	1.08
C17	Hexagon	48%	4	4	12	4	12	4	1%	40%	35%	25%	25%	37%	0.28	0.32	1.08
C18	Hexagon	32%	4	4	12	4	12	4	1%	52%	46%	24%	24%	48%	0.28	0.32	1.08
C19	Hexagon	16%	4	4	12	4	12	4	1%	65%	57%	22%	22%	60%	0.28	0.32	1.08
C81	Hexagon	68%	4	4	12	4	12	4	0%	25%	22%	27%	27%	23%	0.28	0.32	1.08
C82	Hexagon	36%	4	4	12	4	12	4	1%	49%	43%	24%	24%	45%	0.28	0.32	1.08
C83	Hexagon	36%	4	4	12	4	12	4	1%	49%	43%	24%	24%	45%	0.28	0.32	1.08
C84	Hexagon	52%	4	4	12	4	12	4	0%	37%	32%	26%	26%	34%	0.28	0.32	1.08
C85	Hexagon	22%	4	4	12	4	12	4	1%	60%	53%	23%	23%	56%	0.28	0.32	1.08
C91	Hexagon	69%	4	4	12	4	12	4	0%	24%	21%	27%	27%	22%	0.28	0.32	1.08
C92	Hexagon	53%	4	4	12	4	12	4	0%	36%	32%	26%	26%	33%	0.28	0.32	1.08

Panel Layers			Layers						UV %	Visible Light Transmittance	Total Solar Transmittance	Visible Reflectance		Solar Heat Gain Coefficient	U-Value (BTU/hrft2F)		Light to Solar Gain
Panel Type	Shape	Cell Coverage Area	Glass L1 Thickness	Glass L2 Thickness	Spacer Size	Glass L3 Thickness	Spacer Size	Glass L4 Thickness				Exterior	Interior		Winter Nighttime	Summer Daytime	
C74	Triangle	47%	6	6	12	6	12	6	0%	41%	35%	25%	25%	37%	0.28	0.32	1.10
C75	Triangle	37%	6	6	12	6	12	6	0%	49%	42%	24%	24%	44%	0.28	0.32	1.10
C76	Triangle	41%	6	6	12	6	12	6	0%	45%	39%	25%	25%	41%	0.28	0.32	1.10
C17	Hexagon	48%	6	6	12	6	12	6	0%	40%	34%	25%	25%	36%	0.28	0.32	1.10
C18	Hexagon	32%	6	6	12	6	12	6	0%	52%	45%	24%	24%	47%	0.28	0.32	1.10
C19	Hexagon	16%	6	6	12	6	12	6	0%	65%	55%	22%	22%	59%	0.28	0.32	1.10
C81	Hexagon	68%	6	6	12	6	12	6	0%	25%	21%	27%	27%	22%	0.28	0.32	1.10
C82	Hexagon	36%	6	6	12	6	12	6	0%	49%	42%	24%	24%	44%	0.28	0.32	1.10
C83	Hexagon	36%	6	6	12	6	12	6	0%	49%	42%	24%	24%	44%	0.28	0.32	1.10
C84	Hexagon	52%	6	6	12	6	12	6	0%	37%	32%	26%	26%	33%	0.28	0.32	1.10
C85	Hexagon	22%	6	6	12	6	12	6	0%	60%	52%	23%	23%	55%	0.28	0.32	1.10
C91	Hexagon	69%	6	6	12	6	12	6	0%	24%	20%	27%	27%	22%	0.28	0.32	1.10
C92	Hexagon	53%	6	6	12	6	12	6	0%	36%	31%	26%	26%	33%	0.28	0.32	1.10
C93	Hexagon	37%	6	6	12	6	12	6	0%	48%	41%	24%	24%	44%	0.28	0.32	1.10
C94	Hexagon	10%	6	6	12	6	12	6	0%	69%	59%	22%	22%	63%	0.28	0.32	1.10
C95	Hexagon	32%	6	6	12	6	12	6	0%	53%	45%	24%	24%	48%	0.28	0.32	1.10
C96	Hexagon	47%	6	6	12	6	12	6	0%	41%	35%	25%	25%	37%	0.28	0.32	1.10
C101	Parallelogram	63%	6	6	12	6	12	6	0%	28%	24%	27%	27%	26%	0.28	0.32	1.10
C102	Parallelogram	30%	6	6	12	6	12	6	0%	54%	46%	24%	24%	49%	0.28	0.32	1.10
C103	Parallelogram	37%	6	6	12	6	12	6	0%	49%	42%	24%	24%	44%	0.28	0.32	1.10
C104	Parallelogram	32%	6	6	12	6	12	6	0%	53%	45%	24%	24%	48%	0.28	0.32	1.10
C105	Parallelogram	23%	6	6	12	6	12	6	0%	59%	51%	23%	23%	54%	0.28	0.32	1.10
C106	Parallelogram	50%	6	6	12	6	12	6	0%	39%	33%	25%	25%	35%	0.28	0.32	1.10
C111	Parallelogram	53%	6	6	12	6	12	6	0%	36%	31%	26%	26%	33%	0.28	0.32	1.10
C112	Parallelogram	40%	6	6	12	6	12	6	0%	46%	40%	25%	25%	42%	0.28	0.32	1.10
C113	Parallelogram	43%	6	6	12	6	12	6	0%	44%	37%	25%	25%	40%	0.28	0.32	1.10
C114	Parallelogram	27%	6	6	12	6	12	6	0%	57%	48%	23%	23%	51%	0.28	0.32	1.10
C115	Parallelogram	40%	6	6	12	6	12	6	0%	46%	40%	25%	25%	42%	0.28	0.32	1.10
C116	Parallelogram	27%	6	6	12	6	12	6	0%	57%	48%	23%	23%	51%	0.28	0.32	1.10

Panel Layers			Layers						UV %	Visible Light Transmittance	Total Solar Transmittance	Visible Reflectance		Solar Heat Gain Coefficient	U-Value (BTU/hrft2F)		Light to Solar Gain
LowIron-LowIron	Spacer-LowE	Clear-Spacer-LowE	Class L1 Thickness	Class L2 Thickness	Spacer Size	Class L3 Thickness	Spacer Size	Class L4 Thickness				Exterior	Interior		Winter Nighttime	Summer Daytime	
Panel Type	Shape	Cell Coverage Area															
C74	Triangle	47%	3	3	12	3	12	3	0%	31%	13%	22%	21%	21%	0.12	0.12	1.51
C75	Triangle	37%	3	3	12	3	12	3	0%	37%	16%	21%	19%	25%	0.12	0.12	1.51
C76	Triangle	41%	3	3	12	3	12	3	0%	35%	15%	21%	20%	23%	0.12	0.12	1.51
C17	Hexagon	48%	3	3	12	3	12	3	0%	31%	13%	22%	21%	20%	0.12	0.12	1.51
C18	Hexagon	32%	3	3	12	3	12	3	0%	40%	17%	20%	18%	26%	0.12	0.12	1.51
C19	Hexagon	16%	3	3	12	3	12	3	0%	50%	21%	17%	16%	33%	0.12	0.12	1.51
C81	Hexagon	68%	3	3	12	3	12	3	0%	19%	8%	25%	25%	12%	0.12	0.12	1.51
C82	Hexagon	36%	3	3	12	3	12	3	0%	37%	16%	20%	19%	25%	0.12	0.12	1.51
C83	Hexagon	36%	3	3	12	3	12	3	0%	37%	16%	20%	19%	25%	0.12	0.12	1.51
C84	Hexagon	52%	3	3	12	3	12	3	0%	28%	12%	23%	22%	19%	0.12	0.12	1.51
C85	Hexagon	22%	3	3	12	3	12	3	0%	46%	20%	18%	17%	31%	0.12	0.12	1.51
C91	Hexagon	69%	3	3	12	3	12	3	0%	18%	8%	25%	25%	12%	0.12	0.12	1.51
C92	Hexagon	53%	3	3	12	3	12	3	0%	28%	12%	23%	22%	18%	0.12	0.12	1.51
C93	Hexagon	37%	3	3	12	3	12	3	0%	37%	16%	21%	19%	24%	0.12	0.12	1.51
C94	Hexagon	10%	3	3	12	3	12	3	0%	53%	23%	16%	15%	35%	0.12	0.12	1.51
C95	Hexagon	32%	3	3	12	3	12	3	0%	40%	17%	20%	18%	27%	0.12	0.12	1.51
C96	Hexagon	47%	3	3	12	3	12	3	0%	31%	13%	22%	21%	21%	0.12	0.12	1.51
C101	Parallelogram	63%	3	3	12	3	12	3	0%	22%	9%	24%	24%	14%	0.12	0.12	1.51
C102	Parallelogram	30%	3	3	12	3	12	3	0%	41%	18%	19%	18%	27%	0.12	0.12	1.51
C103	Parallelogram	37%	3	3	12	3	12	3	0%	37%	16%	20%	19%	25%	0.12	0.12	1.51
C104	Parallelogram	32%	3	3	12	3	12	3	0%	40%	17%	20%	18%	27%	0.12	0.12	1.51
C105	Parallelogram	23%	3	3	12	3	12	3	0%	45%	19%	18%	17%	30%	0.12	0.12	1.51
C106	Parallelogram	50%	3	3	12	3	12	3	0%	30%	13%	22%	21%	20%	0.12	0.12	1.51
C111	Parallelogram	53%	3	3	12	3	12	3	0%	28%	12%	23%	22%	18%	0.12	0.12	1.51
C112	Parallelogram	40%	3	3	12	3	12	3	0%	35%	15%	21%	20%	23%	0.12	0.12	1.51
C113	Parallelogram	43%	3	3	12	3	12	3	0%	33%	14%	21%	20%	22%	0.12	0.12	1.51
C114	Parallelogram	27%	3	3	12	3	12	3	0%	43%	18%	19%	18%	29%	0.12	0.12	1.51
C115	Parallelogram	40%	3	3	12	3	12	3	0%	35%	15%	21%	20%	23%	0.12	0.12	1.51
C116	Parallelogram	27%	3	3	12	3	12	3	0%	43%	18%	19%	18%	29%	0.12	0.12	1.51

LLSCSCL4

Panel Layers			Layers						UV %	Visible Light Transmittance	Total Solar Transmittance	Visible Reflectance		Solar Heat Gain Coefficient	U-Value (BTU/hrft2F)		Light to Solar Gain
Panel Type	Shape	Cell Coverage Area	Class L1 Thickness	Class L2 Thickness	Spacer Size	Class L3 Thickness	Spacer Size	Class L4 Thickness				Exterior	Interior		Winter Nighttime	Summer Daytime	
C74	Triangle	47%	4	4	12	4	12	4	0%	31%	13%	22%	21%	21%	0.12	0.12	1.49
C75	Triangle	37%	4	4	12	4	12	4	0%	37%	16%	20%	19%	25%	0.12	0.12	1.49
C76	Triangle	41%	4	4	12	4	12	4	0%	34%	15%	21%	19%	23%	0.12	0.12	1.49
C17	Hexagon	48%	4	4	12	4	12	4	0%	30%	13%	22%	21%	20%	0.12	0.12	1.49
C18	Hexagon	32%	4	4	12	4	12	4	0%	39%	17%	19%	18%	26%	0.12	0.12	1.49
C19	Hexagon	16%	4	4	12	4	12	4	0%	49%	21%	17%	15%	33%	0.12	0.12	1.49
C81	Hexagon	68%	4	4	12	4	12	4	0%	19%	8%	25%	24%	12%	0.12	0.12	1.49
C82	Hexagon	36%	4	4	12	4	12	4	0%	37%	16%	20%	19%	25%	0.12	0.12	1.49
C83	Hexagon	36%	4	4	12	4	12	4	0%	37%	16%	20%	19%	25%	0.12	0.12	1.49
C84	Hexagon	52%	4	4	12	4	12	4	0%	28%	12%	22%	21%	19%	0.12	0.12	1.49
C85	Hexagon	22%	4	4	12	4	12	4	0%	45%	20%	17%	16%	31%	0.12	0.12	1.49
C91	Hexagon	69%	4	4	12	4	12	4	0%	18%	8%	25%	24%	12%	0.12	0.12	1.49
C92	Hexagon	53%	4	4	12	4	12	4	0%	27%	12%	23%	22%	18%	0.12	0.12	1.49

Panel Layers			Layers						UV %	Visible Light Transmittance	Total Solar Transmittance	Visible Reflectance		Solar Heat Gain Coefficient	U-Value (BTU/hrft2F)		Light to Solar Gain
Panel Type	Shape	Cell Coverage Area	Class L1 Thickness	Class L2 Thickness	Spacer Size	Class L3 Thickness	Spacer Size	Class L4 Thickness				Exterior	Interior		Winter Nighttime	Summer Daytime	
C74	Triangle	47%	6	6	12	6	12	6	0%	30%	13%	22%	21%	20%	0.12	0.12	1.50
C75	Triangle	37%	6	6	12	6	12	6	0%	36%	15%	20%	19%	24%	0.12	0.12	1.50
C76	Triangle	41%	6	6	12	6	12	6	0%	33%	14%	21%	19%	22%	0.12	0.12	1.50
C17	Hexagon	48%	6	6	12	6	12	6	0%	29%	12%	22%	21%	20%	0.12	0.12	1.50
C18	Hexagon	32%	6	6	12	6	12	6	0%	39%	16%	19%	18%	26%	0.12	0.12	1.50
C19	Hexagon	16%	6	6	12	6	12	6	0%	48%	20%	17%	15%	32%	0.12	0.12	1.50
C81	Hexagon	68%	6	6	12	6	12	6	0%	18%	8%	25%	24%	12%	0.12	0.12	1.50
C82	Hexagon	36%	6	6	12	6	12	6	0%	36%	15%	20%	19%	24%	0.12	0.12	1.50
C83	Hexagon	36%	6	6	12	6	12	6	0%	36%	15%	20%	19%	24%	0.12	0.12	1.50
C84	Hexagon	52%	6	6	12	6	12	6	0%	27%	11%	22%	21%	18%	0.12	0.12	1.50
C85	Hexagon	22%	6	6	12	6	12	6	0%	45%	19%	17%	16%	30%	0.12	0.12	1.50
C91	Hexagon	69%	6	6	12	6	12	6	0%	18%	7%	25%	24%	12%	0.12	0.12	1.50
C92	Hexagon	53%	6	6	12	6	12	6	0%	27%	11%	23%	22%	18%	0.12	0.12	1.50
C93	Hexagon	37%	6	6	12	6	12	6	0%	36%	15%	20%	19%	24%	0.12	0.12	1.50
C94	Hexagon	10%	6	6	12	6	12	6	0%	51%	22%	16%	14%	34%	0.12	0.12	1.50
C95	Hexagon	32%	6	6	12	6	12	6	0%	39%	16%	19%	18%	26%	0.12	0.12	1.50
C96	Hexagon	47%	6	6	12	6	12	6	0%	30%	13%	22%	21%	20%	0.12	0.12	1.50
C101	Parallelogram	63%	6	6	12	6	12	6	0%	21%	9%	24%	23%	14%	0.12	0.12	1.50
C102	Parallelogram	30%	6	6	12	6	12	6	0%	40%	17%	19%	17%	27%	0.12	0.12	1.50
C103	Parallelogram	37%	6	6	12	6	12	6	0%	36%	15%	20%	19%	24%	0.12	0.12	1.50
C104	Parallelogram	32%	6	6	12	6	12	6	0%	39%	16%	19%	18%	26%	0.12	0.12	1.50
C105	Parallelogram	23%	6	6	12	6	12	6	0%	44%	18%	18%	16%	29%	0.12	0.12	1.50
C106	Parallelogram	50%	6	6	12	6	12	6	0%	29%	12%	22%	21%	19%	0.12	0.12	1.50
C111	Parallelogram	53%	6	6	12	6	12	6	0%	27%	11%	23%	22%	18%	0.12	0.12	1.50
C112	Parallelogram	40%	6	6	12	6	12	6	0%	34%	14%	20%	19%	23%	0.12	0.12	1.50
C113	Parallelogram	43%	6	6	12	6	12	6	0%	32%	14%	21%	20%	22%	0.12	0.12	1.50
C114	Parallelogram	27%	6	6	12	6	12	6	0%	42%	18%	18%	17%	28%	0.12	0.12	1.50
C115	Parallelogram	40%	6	6	12	6	12	6	0%	34%	14%	20%	19%	23%	0.12	0.12	1.50
C116	Parallelogram	27%	6	6	12	6	12	6	0%	42%	18%	18%	17%	28%	0.12	0.12	1.50

Panel Layers			Layers						UV %	Visible Light Transmittance	Total Solar Transmittance	Visible Reflectance		Solar Heat Gain Coefficient	U-Value (BTU/hrft2F)		Light to Solar Gain
Panel Type	Shape	Cell Coverage Area	Glass L1 Thickness	Glass L2 Thickness	Spacer Size	Glass L3 Thickness	Spacer Size	Glass L4 Thickness				Exterior	Interior		Winter Nighttime	Summer Daytime	
C74	Triangle	47%	3	3	12	3	12	3	0%	32%	14%	22%	21%	21%	0.12	0.12	1.53
C75	Triangle	37%	3	3	12	3	12	3	0%	38%	17%	21%	19%	25%	0.12	0.12	1.53
C76	Triangle	41%	3	3	12	3	12	3	0%	36%	16%	21%	20%	23%	0.12	0.12	1.53
C17	Hexagon	48%	3	3	12	3	12	3	0%	32%	14%	22%	21%	21%	0.12	0.12	1.53
C18	Hexagon	32%	3	3	12	3	12	3	0%	41%	18%	20%	18%	27%	0.12	0.12	1.53
C19	Hexagon	16%	3	3	12	3	12	3	0%	51%	23%	17%	16%	34%	0.12	0.12	1.53
C81	Hexagon	68%	3	3	12	3	12	3	0%	20%	9%	25%	25%	13%	0.12	0.12	1.53
C82	Hexagon	36%	3	3	12	3	12	3	0%	39%	17%	20%	19%	25%	0.12	0.12	1.53
C83	Hexagon	36%	3	3	12	3	12	3	0%	39%	17%	20%	19%	25%	0.12	0.12	1.53
C84	Hexagon	52%	3	3	12	3	12	3	0%	29%	13%	23%	22%	19%	0.12	0.12	1.53
C85	Hexagon	22%	3	3	12	3	12	3	0%	48%	21%	18%	17%	31%	0.12	0.12	1.53
C91	Hexagon	69%	3	3	12	3	12	3	0%	19%	8%	25%	25%	12%	0.12	0.12	1.53
C92	Hexagon	53%	3	3	12	3	12	3	0%	29%	13%	23%	22%	19%	0.12	0.12	1.53
C93	Hexagon	37%	3	3	12	3	12	3	0%	38%	17%	21%	19%	25%	0.12	0.12	1.53
C94	Hexagon	10%	3	3	12	3	12	3	0%	55%	24%	16%	15%	36%	0.12	0.12	1.53
C95	Hexagon	32%	3	3	12	3	12	3	0%	42%	18%	20%	18%	27%	0.12	0.12	1.53
C96	Hexagon	47%	3	3	12	3	12	3	0%	32%	14%	22%	21%	21%	0.12	0.12	1.53
C101	Parallelogram	63%	3	3	12	3	12	3	0%	22%	10%	24%	24%	15%	0.12	0.12	1.53
C102	Parallelogram	30%	3	3	12	3	12	3	0%	43%	19%	19%	18%	28%	0.12	0.12	1.53
C103	Parallelogram	37%	3	3	12	3	12	3	0%	39%	17%	20%	19%	25%	0.12	0.12	1.53
C104	Parallelogram	32%	3	3	12	3	12	3	0%	42%	18%	20%	18%	27%	0.12	0.12	1.53
C105	Parallelogram	23%	3	3	12	3	12	3	0%	47%	21%	18%	17%	31%	0.12	0.12	1.53
C106	Parallelogram	50%	3	3	12	3	12	3	0%	31%	14%	22%	21%	20%	0.12	0.12	1.53
C111	Parallelogram	53%	3	3	12	3	12	3	0%	29%	13%	23%	22%	19%	0.12	0.12	1.53
C112	Parallelogram	40%	3	3	12	3	12	3	0%	37%	16%	21%	20%	24%	0.12	0.12	1.53
C113	Parallelogram	43%	3	3	12	3	12	3	0%	35%	15%	21%	20%	23%	0.12	0.12	1.53
C114	Parallelogram	27%	3	3	12	3	12	3	0%	45%	20%	19%	18%	29%	0.12	0.12	1.53
C115	Parallelogram	40%	3	3	12	3	12	3	0%	37%	16%	21%	20%	24%	0.12	0.12	1.53
C116	Parallelogram	27%	3	3	12	3	12	3	0%	45%	20%	19%	18%	29%	0.12	0.12	1.53

Table with columns: Panel Layers, Lowiron-Lowiron-Spacer-LowLowiron-Spacer-LowLowiron, Layers (Glass L1, Glass L2, Spacer Size, Glass L3, Spacer Size, Glass L4), UV %, Visible Light Transmittance, Total Solar Transmittance, Visible Reflectance (Exterior, Interior), Solar Heat Gain Coefficient, U-Value (BTU/h/ft2) (Winter Nighttime, Summer Daytime), and Light to Solar Gain.

Panel Layers			Layers						UV %	Visible Light Transmittance	Total Solar Transmittance	Visible Reflectance		Solar Heat Gain Coefficient	U-Value (BTU/hrft2F)		Light to Solar Gain
Panel Type	Shape	Cell Coverage Area	Glass L1 Thickness	Glass L2 Thickness	Spacer Size	Glass L3 Thickness	Spacer Size	Glass L4 Thickness				Exterior	Interior		Winter Nighttime	Summer Daytime	
C74	Triangle	47%	4	4	12	4	12	4	0%	32%	14%	22%	21%	21%	0.12	0.12	1.53
C75	Triangle	37%	4	4	12	4	12	4	0%	38%	17%	21%	19%	25%	0.12	0.12	1.53
C76	Triangle	41%	4	4	12	4	12	4	0%	36%	16%	21%	20%	23%	0.12	0.12	1.53
C17	Hexagon	48%	4	4	12	4	12	4	0%	32%	14%	22%	21%	21%	0.12	0.12	1.53
C18	Hexagon	32%	4	4	12	4	12	4	0%	41%	18%	20%	18%	27%	0.12	0.12	1.53
C19	Hexagon	16%	4	4	12	4	12	4	0%	51%	23%	17%	16%	34%	0.12	0.12	1.53
C81	Hexagon	68%	4	4	12	4	12	4	0%	20%	9%	25%	25%	13%	0.12	0.12	1.53
C82	Hexagon	36%	4	4	12	4	12	4	0%	39%	17%	20%	19%	25%	0.12	0.12	1.53
C83	Hexagon	36%	4	4	12	4	12	4	0%	39%	17%	20%	19%	25%	0.12	0.12	1.53
C84	Hexagon	52%	4	4	12	4	12	4	0%	29%	13%	23%	22%	19%	0.12	0.12	1.53
C85	Hexagon	22%	4	4	12	4	12	4	0%	48%	21%	18%	17%	31%	0.12	0.12	1.53
C91	Hexagon	69%	4	4	12	4	12	4	0%	19%	8%	25%	25%	12%	0.12	0.12	1.53
C92	Hexagon	53%	4	4	12	4	12	4	0%	29%	13%	23%	22%	19%	0.12	0.12	1.53
C93	Hexagon	37%	4	4	12	4	12	4	0%	38%	17%	21%	19%	25%	0.12	0.12	1.53
C94	Hexagon	10%	4	4	12	4	12	4	0%	55%	24%	16%	15%	36%	0.12	0.12	1.53
C95	Hexagon	32%	4	4	12	4	12	4	0%	42%	18%	20%	18%	27%	0.12	0.12	1.53
C96	Hexagon	47%	4	4	12	4	12	4	0%	32%	14%	22%	21%	21%	0.12	0.12	1.53
C101	Parallelogram	63%	4	4	12	4	12	4	0%	22%	10%	24%	24%	15%	0.12	0.12	1.53
C102	Parallelogram	30%	4	4	12	4	12	4	0%	43%	19%	19%	18%	28%	0.12	0.12	1.53
C103	Parallelogram	37%	4	4	12	4	12	4	0%	39%	17%	20%	19%	25%	0.12	0.12	1.53
C104	Parallelogram	32%	4	4	12	4	12	4	0%	42%	18%	20%	18%	27%	0.12	0.12	1.53
C105	Parallelogram	23%	4	4	12	4	12	4	0%	47%	21%	18%	17%	31%	0.12	0.12	1.53
C106	Parallelogram	50%	4	4	12	4	12	4	0%	31%	14%	22%	21%	20%	0.12	0.12	1.53
C111	Parallelogram	53%	4	4	12	4	12	4	0%	29%	13%	23%	22%	19%	0.12	0.12	1.53
C112	Parallelogram	40%	4	4	12	4	12	4	0%	37%	16%	21%	20%	24%	0.12	0.12	1.53
C113	Parallelogram	43%	4	4	12	4	12	4	0%	35%	15%	21%	20%	23%	0.12	0.12	1.53
C114	Parallelogram	27%	4	4	12	4	12	4	0%	45%	20%	19%	18%	29%	0.12	0.12	1.53
C115	Parallelogram	40%	4	4	12	4	12	4	0%	37%	16%	21%	20%	24%	0.12	0.12	1.53
C116	Parallelogram	27%	4	4	12	4	12	4	0%	45%	20%	19%	18%	29%	0.12	0.12	1.53


Panel Layers			Layers						UV %	Visible Light Transmittance	Total Solar Transmittance	Visible Reflectance		Solar Heat Gain Coefficient	U-Value (BTU/hrft ² F)		Light to Solar Gain
Panel Type	Shape	Cell Coverage Area	Class L1 Thickness	Class L2 Thickness	Spacer Size	Class L3 Thickness	Spacer Size	Class L4 Thickness				Exterior	Interior		Winter Nighttime	Summer Daytime	
C74	Triangle	47%	6	6	12	6	12	6	0%	32%	14%	22%	21%	21%	0.12	0.12	1.54
C75	Triangle	37%	6	6	12	6	12	6	0%	38%	17%	22%	19%	25%	0.12	0.12	1.54
C76	Triangle	41%	6	6	12	6	12	6	0%	35%	16%	21%	20%	23%	0.12	0.12	1.54
C17	Hexagon	48%	6	6	12	6	12	6	0%	31%	14%	22%	21%	20%	0.12	0.12	1.54
C18	Hexagon	32%	6	6	12	6	12	6	0%	41%	18%	20%	18%	26%	0.12	0.12	1.54
C19	Hexagon	16%	6	6	12	6	12	6	0%	50%	23%	17%	16%	33%	0.12	0.12	1.54
C81	Hexagon	68%	6	6	12	6	12	6	0%	19%	9%	25%	25%	12%	0.12	0.12	1.54
C82	Hexagon	36%	6	6	12	6	12	6	0%	38%	17%	20%	19%	25%	0.12	0.12	1.54
C83	Hexagon	36%	6	6	12	6	12	6	0%	38%	17%	20%	19%	25%	0.12	0.12	1.54
C84	Hexagon	52%	6	6	12	6	12	6	0%	29%	13%	23%	22%	19%	0.12	0.12	1.54
C85	Hexagon	22%	6	6	12	6	12	6	0%	47%	21%	18%	17%	31%	0.12	0.12	1.54
C91	Hexagon	69%	6	6	12	6	12	6	0%	19%	8%	25%	25%	12%	0.12	0.12	1.54
C92	Hexagon	53%	6	6	12	6	12	6	0%	28%	13%	23%	22%	18%	0.12	0.12	1.54
C93	Hexagon	37%	6	6	12	6	12	6	0%	38%	17%	21%	19%	24%	0.12	0.12	1.54
C94	Hexagon	10%	6	6	12	6	12	6	0%	54%	24%	16%	15%	35%	0.12	0.12	1.54
C95	Hexagon	32%	6	6	12	6	12	6	0%	41%	18%	20%	18%	27%	0.12	0.12	1.54
C96	Hexagon	47%	6	6	12	6	12	6	0%	32%	14%	22%	21%	21%	0.12	0.12	1.54
C101	Parallelogram	63%	6	6	12	6	12	6	0%	22%	10%	24%	24%	14%	0.12	0.12	1.54
C102	Parallelogram	30%	6	6	12	6	12	6	0%	42%	19%	19%	18%	27%	0.12	0.12	1.54
C103	Parallelogram	37%	6	6	12	6	12	6	0%	38%	17%	20%	19%	25%	0.12	0.12	1.54
C104	Parallelogram	32%	6	6	12	6	12	6	0%	41%	18%	20%	18%	27%	0.12	0.12	1.54
C105	Parallelogram	23%	6	6	12	6	12	6	0%	46%	21%	18%	17%	30%	0.12	0.12	1.54
C106	Parallelogram	50%	6	6	12	6	12	6	0%	30%	14%	22%	21%	20%	0.12	0.12	1.54
C111	Parallelogram	53%	6	6	12	6	12	6	0%	28%	13%	23%	22%	18%	0.12	0.12	1.54
C112	Parallelogram	40%	6	6	12	6	12	6	0%	36%	16%	21%	20%	23%	0.12	0.12	1.54
C113	Parallelogram	43%	6	6	12	6	12	6	0%	34%	15%	21%	20%	22%	0.12	0.12	1.54
C114	Parallelogram	27%	6	6	12	6	12	6	0%	44%	20%	19%	18%	29%	0.12	0.12	1.54
C115	Parallelogram	40%	6	6	12	6	12	6	0%	36%	16%	21%	20%	23%	0.12	0.12	1.54
C116	Parallelogram	27%	6	6	12	6	12	6	0%	44%	20%	19%	18%	29%	0.12	0.12	1.54



LEARN MORE:


MITREX.COM

 info@mitrex.com

 +1-855-254-0214 (Toll Free)


Headquarters:

 41 Racine Rd., Toronto,
ON M9W 2Z4, Canada


 +1 (416) 497 7120

USA:

 10880 Wilshire Blvd Suite 1101,
Los Angeles, CA 90024, USA

 +1 (323) 301 7978

 1 Rockefeller Plaza Fl 11,
New York, NY 10020, USA

 +1 (646) 583 4486